

Kennametal Stellite Stellite® 31 PM after P/M processing, aged 8 hours at 802°C air cooled

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

Material Notes:

Typical applications include vane plugs, fuel metering pins, spacer bushings, ball bearing blanks, race bearing blanks, diesel engine exhaust, fluid valve seats, saw cutter inserts, miscellaneous wear parts. Data provided by the manufacturer, Deloro Stellite Inc. Product of former Deloro Stellite Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kennametal-Stellite-Stellite-31-PM-after-PM-processing-aged-8-hours-at-802C-air-cooled.php

Physical Properties	Metric	English	Comments
Density	8.45 g/cc	0.305 lb/in ³	P/M (98%)
	8.61 g/cc	0.311 lb/in ³	Theoretical

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1035 MPa	150100 psi	
Tensile Strength, Yield	725 MPa @Strain 0.200 %	105000 psi @Strain 0.200 %	
Elongation at Break	1.5 %	1.5 %	in 25.4 mm

Thermal Properties	Metric	English	Comments
CTE, linear	14.1 µm/m-°C	7.83 µin/in-°F	
	@Temperature 21.0 - 316 °C	@Temperature 69.8 - 601 °F	
	14.5 µm/m-°C	8.06 µin/in-°F	
	@Temperature 21.0 - 427 °C	@Temperature 69.8 - 801 °F	
	15.1 µm/m-°C	8.39 µin/in-°F	
	@Temperature 21.0 - 538 °C	@Temperature 69.8 - 1000 °F	
	15.7 µm/m-°C	8.72 µin/in-°F	
	@Temperature 21.1 - 649 °C	@Temperature 70.0 - 1200 °F	
	16.5 µm/m-°C	9.17 µin/in-°F	
	@Temperature 21.1 - 816 °C	@Temperature 70.0 - 1500 °F	

Thermal Properties	Metric 15.5 μm/m-°C	English 8.22 μin/in-°F	Comments
	@Temperature 21.1 - 871 °C	@Temperature 70.0 - 1600 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.50 %	0.50 %	
Chromium, Cr	25.5 %	25.5 %	
Cobalt, Co	50 %	50 %	As remainder
Iron, Fe	<= 2.0 %	<= 2.0 %	
Manganese, Mn	<= 1.0 %	<= 1.0 %	
Nickel, Ni	10.5 %	10.5 %	
Other	<= 2.0 %	<= 2.0 %	
Phosphorous, P	<= 0.040 %	<= 0.040 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	<= 0.040 %	<= 0.040 %	
Tungsten, W	7.5 %	7.5 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China