

## Kinetics MIM 17-4PH Stainless Steel (H1100 Condition)

Category : Metal , Ferrous Metal , Stainless Steel , Precipitation Hardening Stainless

### Material Notes:

Precipitation-hardening stainless steel. Offers a good balance between corrosion resistance and strength. Magnetic. Hardenable to various strength levels and hardness by varying the aging heat treat temperature. Typically provides better corrosion resistance than the 400 series stainless steels, and better strength than the 300 series stainless steels. Often used for aircraft, dental, marine, medical, surgical, and applications where high levels of strength and hardness, and good corrosion resistance is required. Property values reported are typical for Kinetics' MIM products. Metal Injection Molding General Notes: Fine metal powders (generally

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kinetics-MIM-17-4PH-Stainless-Steel-H1100-Condition.php](http://www.lookpolymers.com/polymer_Kinetics-MIM-17-4PH-Stainless-Steel-H1100-Condition.php)

Physical Properties	Metric	English	Comments
Density	7.70 g/cc	0.278 lb/in <sup>3</sup>	Sintered

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	34	34	
Tensile Strength, Ultimate	1000 MPa	145000 psi	
Tensile Strength, Yield	910 MPa	132000 psi	
Elongation at Break	12 %	12 %	in 1 inch
Reduction of Area	33 %	33 %	
Charpy Impact, Unnotched	140 J	103 ft-lb	1/2 size bar

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.070 %	<= 0.070 %	
Chromium, Cr	15.5 - 17.5 %	15.5 - 17.5 %	
Copper, Cu	3.0 - 5.0 %	3.0 - 5.0 %	
Iron, Fe	70 - 78.4 %	70 - 78.4 %	by difference
Manganese, Mn	<= 1.0 %	<= 1.0 %	
Nb + Ta	0.15 - 0.45 %	0.15 - 0.45 %	
Nickel, Ni	3.0 - 5.0 %	3.0 - 5.0 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	

Descriptive Properties	Value	Comments
Surface Finish	30 Ra	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China