

Kingfa JH710 G10D Flame Retardant & 10% Glass Fiber Reinforced PC

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Glass Fiber Filled, Flame Retardant

Material Notes:

Features: Environmental friendly flame retardant UL V-0 @ 1.6mm High mechanical strength Good size stability, good surface Suitable for exact molding Applications: Exact mechanism parts Electrical and electronic parts Printer, photocopier cabinet Electrical equipment parts Information Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-JH710-G10D-Flame-Retardant-10-Glass-Fiber-Reinforced-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	ASTM D792
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	83	83	ASTM D785
Tensile Strength at Break	54.0 MPa	7830 psi	10mm/min; ASTM D638
Elongation at Break	18 %	18 %	10mm/min; ASTM D638
Flexural Strength	92.0 MPa	13300 psi	2mm/min; ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	2mm/min; ASTM D790
Izod Impact, Notched	1.16 J/cm	2.17 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	
Izod Impact, Unnotched	4.50 J/cm - NB	8.43 ft-lb/in - NB	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	130 Â°C	266 Â°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	122 Â°C	252 Â°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Thermal Properties	V-0 Metric	V-0 English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257
Dielectric Strength	19.0 kV/mm	483 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	<= 290 Â°C	<= 554 Â°F	
Rear Barrel Temperature	235 - 260 Â°C	455 - 500 Â°F	Start Point: 245Â°C
Middle Barrel Temperature	240 - 270 Â°C	464 - 518 Â°F	Start Point: 250Â°C
Front Barrel Temperature	250 - 280 Â°C	482 - 536 Â°F	Start Point: 255Â°C
Melt Temperature	235 - 260 Â°C	455 - 500 Â°F	Start Point: 245Â°C
Mold Temperature	80.0 - 130 Â°C	176 - 266 Â°F	Start Point: 90Â°C
Drying Temperature	110 - 120 Â°C @Time 14400 - 21600 sec	230 - 248 Â°F @Time 4.00 - 6.00 hour	Pre-dry
Back Pressure	0.000 - 10.0 MPa	0.000 - 1450 psi	

Descriptive Properties	Value	Comments
Glass Fiber Content (%)	10	
Injection Speed	60-90%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China