

Kingfa MAC-601 AC PC/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Features:Excellent balance propertiesHigh impact strengthGood processing propertiesApplications:Injection moldingAutomobile instrument panelElectrical and electronic partsComputer and accessoriesHousehold appliance thin wall partsInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-MAC-601-AC-PCABS-Alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Water Absorption	0.30 %	0.30 %	ASTM D570
	@Temperature 23.0 Å°C, Time 86400 sec	@Temperature 73.4 Å°F, Time 24.0 hour	
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	50.0 MPa	7250 psi	50mm/min; ASTM D638
Elongation at Break	70 %	70 %	50mm/min; ASTM D638
Flexural Strength	80.0 MPa	11600 psi	2mm/min; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2mm/min; ASTM D790
Izod Impact, Notched	5.00 J/cm	9.37 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Å°C	@Thickness 0.126 in, Temperature 73.4 Å°F	
Izod Impact, Unnotched	NB	NB	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Å°C	@Thickness 0.126 in, Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 Å°C	257 Å°F	ASTM D648

Thermal Properties	@Thickness 6.40 mm Metric	@Thickness 0.252 in English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	105 Â°C @Thickness 6.40 mm	221 Â°F @Thickness 0.252 in	ASTM D648
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257
Dielectric Strength	>= 35.0 kV/mm	>= 889 kV/in	1.6mm; ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	<= 280 Â°C	<= 536 Â°F	
Rear Barrel Temperature	230 - 250 Â°C	446 - 482 Â°F	Start Point: 230Â°C
Middle Barrel Temperature	240 - 260 Â°C	464 - 500 Â°F	Start Point: 235Â°C
Front Barrel Temperature	250 - 280 Â°C	482 - 536 Â°F	Start Point: 240Â°C
Melt Temperature	240 - 280 Â°C	464 - 536 Â°F	Start Point: 245Â°C
Mold Temperature	60.0 - 90.0 Â°C	140 - 194 Â°F	Start Point: 60Â°C
Drying Temperature	100 - 110 Â°C @Time 14400 - 21600 sec	212 - 230 Â°F @Time 4.00 - 6.00 hour	Pre-dry
Back Pressure	0.700 - 1.00 MPa	102 - 145 psi	

Descriptive Properties	Value	Comments
Injection Speed	60-100%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China