

Kingfa MAC-601 UV PC/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Features:Excellent balance propertiesHigh impact strengthGood processing propertiesApplications:Injection moldingAutomobile instrument panelElectrical and electronic partsComputer and accessoriesHousehold appliance thin wall partsInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-MAC-601-UV-PCABS-Alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc @Temperature 23.0 Â°C	1.13 g/cc @Temperature 73.4 Â°F	ASTM D792
Water Absorption	0.30 % @Temperature 23.0 Â°C, Time 86400 sec	0.30 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm @Temperature 23.0 Â°C	0.0030 - 0.0070 in/in @Temperature 73.4 Â°F	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	50.0 MPa	7250 psi	50mm/min; ASTM D638
Elongation at Break	60 %	60 %	50mm/min; ASTM D638
Flexural Strength	75.0 MPa	10900 psi	2mm/min; ASTM D790
Flexural Modulus	2.10 GPa	305 ksi	2mm/min; ASTM D790
Izod Impact, Notched	5.00 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	9.37 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.20 mm, Temperature 23.0 Â°C	NB @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 Â°C	257 Â°F	ASTM D648

Thermal Properties	@Thickness 6.40 mm Metric	@Thickness 0.252 in English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	105 Å°C @Thickness 6.40 mm	221 Å°F @Thickness 0.252 in	ASTM D648
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257
Dielectric Strength	>= 35.0 kV/mm	>= 889 kV/in	1.6mm; ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	<= 280 Å°C	<= 536 Å°F	
Rear Barrel Temperature	230 - 250 Å°C	446 - 482 Å°F	Start Point: 230Å°C
Middle Barrel Temperature	240 - 260 Å°C	464 - 500 Å°F	Start Point: 235Å°C
Front Barrel Temperature	250 - 280 Å°C	482 - 536 Å°F	Start Point: 240Å°C
Melt Temperature	240 - 280 Å°C	464 - 536 Å°F	Start Point: 245Å°C
Mold Temperature	60.0 - 90.0 Å°C	140 - 194 Å°F	Start Point: 60Å°C
Drying Temperature	100 - 110 Å°C @Time 14400 - 21600 sec	212 - 230 Å°F @Time 4.00 - 6.00 hour	Pre-dry
Back Pressure	0.700 - 1.00 MPa	102 - 145 psi	

Descriptive Properties	Value	Comments
Injection Speed	60-100%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China