

Kingfa PBT-RG152 Flame Retardant, 15% Glass Fiber Reinforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

Features: Flame retardant High strength High temperature properties High glossy Good surface No blooming Applications: Injection molding Connectors Relay Bobbins Plugs E & E parts Information Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-PBT-RG152-Flame-Retardant-15-Glass-Fiber-Reinforced-PBT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.55 g/cc @Temperature 23.0 Â°C	1.55 g/cc @Temperature 73.4 Â°F	ASTM D792
Water Absorption	0.070 % @Temperature 23.0 Â°C, Time 86400 sec	0.070 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0050 - 0.011 cm/cm @Temperature 23.0 Â°C	0.0050 - 0.011 in/in @Temperature 73.4 Â°F	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength at Break	95.0 MPa	13800 psi	10mm/min; ASTM D638
Elongation at Break	3.4 %	3.4 %	10mm/min; ASTM D638
Flexural Strength	150 MPa	21800 psi	2mm/min; ASTM D790
Flexural Modulus	5.60 GPa	812 ksi	2mm/min; ASTM D790
Izod Impact, Notched	0.700 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	1.31 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	215 Â°C @Thickness 6.40 mm	419 Â°F @Thickness 0.252 in	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	205 Â°C @Thickness 6.40 mm	401 Â°F @Thickness 0.252 in	ASTM D648

Thermal Properties Flammability, UL94	^{V-0} Metric	^{V-0} English	Comments
	@Thickness 0.700 mm	@Thickness 0.0276 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	<= 265 Â°C	<= 509 Â°F	
Rear Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	Start Point: 235Â°C
Middle Barrel Temperature	235 - 255 Â°C	455 - 491 Â°F	Start Point: 245Â°C
Front Barrel Temperature	240 - 265 Â°C	464 - 509 Â°F	Start Point: 255Â°C
Melt Temperature	240 - 260 Â°C	464 - 500 Â°F	Start Point: 250Â°C
Mold Temperature	50.0 - 70.0 Â°C	122 - 158 Â°F	Start Point: 60Â°C
Drying Temperature	120 - 140 Â°C @Time 14400 - 21600 sec	248 - 284 Â°F @Time 4.00 - 6.00 hour	Pre-dry

Descriptive Properties	Value	Comments
Glass Fiber Content (%)	15	
Injection Speed	Moderate to High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China