

Kolon KOPAA® KN1322VO Flame Retardant Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Unreinforced, Flame Retardant

Material Notes:

KOPAA® is a thermoplastic resin with excellent mechanical, thermal and electrical properties and is widely used in automobile and industrial parts. Good mechanical properties, outstanding self-lubrication and abrasion resistance, excellent chemical resistance, wide usage temperature, good impact absorbing characteristics. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOPA-KN1322VO-Flame-Retardant-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	DIN 53479; ASTM D792
Water Absorption	1.4 %	1.4 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.014 - 0.018 cm/cm	0.014 - 0.018 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	DIN 53505; ASTM D785
Tensile Strength, Ultimate	83.4 MPa	12100 psi	DIN 53455; ASTM D638
Elongation at Break	40 %	40 %	DIN 53455; ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	DIN 53455; ASTM D790
Flexural Modulus	3.04 GPa	441 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.686 J/cm	1.29 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C @Temperature 20.0 °C	50.0 µin/in-°F @Temperature 68.0 °F	DIN 53752; ASTM D696
Melting Point	220 °C	428 °F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	190 °C	374 °F	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	DIN 53461; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	^{3.4} Metric	^{3.4} English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	ASTM D149/DIN 53483
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149/DIN 53481
Arc Resistance	115 sec	115 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China