

Kolon KOPAA® KN333G15HI Multi Reinforced Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

KOPAA® is a thermoplastic resin with excellent mechanical, thermal and electrical properties and is widely used in the automobile, electrical and industrial parts. High tensile strength, outstanding self lubrication and abrasion resistance, excellent chemical & weather resistance, high usage temperature. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOPA-KN333G15HI-Multi-Reinforced-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	DIN 53479; ASTM D792
Water Absorption	0.40 %	0.40 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	DIN 53505; ASTM D785
Tensile Strength, Ultimate	98.1 MPa	14200 psi	DIN 53455; ASTM D638
Elongation at Break	8.0 %	8.0 %	DIN 53455; ASTM D638
Flexural Yield Strength	157 MPa	22800 psi	DIN 53455; ASTM D790
Flexural Modulus	3.92 GPa	569 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	1.67 J/cm	3.12 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 µm/m-°C @Temperature 20.0 °C	27.8 µin/in-°F @Temperature 68.0 °F	DIN 53752; ASTM D696
Melting Point	255 °C	491 °F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	235 °C	455 °F	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	^{3.4} Metric	^{3.4} English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	ASTM D149/DIN 53483
Dielectric Strength	21.0 kV/mm	533 kV/in	ASTM D149/DIN 53481
Arc Resistance	130 sec	130 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China