

Kraton® G7820 GU-N (SEBS) Compound

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Description: Kraton G7820 GU-N is an easy processing, general purpose 90 Shore A hardness material designed for a wide variety of applications. It is supplied from North America in the physical form identified: Kraton G7820 GU-N - supplied as a dense, natural color pellet
Region: North America; Asia Pacific; Europe; Japan; and South America
Applications: Compounding and Personal Hygiene; Adhesives, Sealant and Coatings; Bitumen Modification; Footwear; and Impact Modification
Information provided by Kraton®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kraton-G7820-GU-N-SEBS-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 - 1.17 g/cc	1.11 - 1.17 g/cc	BAM 1014

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85 - 95	85 - 95	BAM 1003
Tensile Strength	12.07 MPa	1751 psi	ASTM D412
	22.3 MPa	3230 psi	After Heat Aging 168 hrs at 150°C; ASTM D412
Elongation at Break	650 %	650 %	ASTM D412
	730 %	730 %	After Heat Aging 168 hrs at 150°C; ASTM D573
300% Modulus	0.00621 GPa	0.901 ksi	ASTM D412
Tear Strength	49.1 kN/m	280 pli	Die C; ASTM D624
Compression Set	27 %	27 %	
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	ASTM D395B
	64 %	64 %	
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	ASTM D395B

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-52.0 °C	-61.6 °F	ASTM D746
Flame Spread	55.9 mm/min	2.20 in/min	FVSS302/SAE J369 in/min

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	193 - 204 Â°C	380 - 400 Â°F	
Front Barrel Temperature	204 - 216 Â°C	400 - 420 Â°F	
Nozzle Temperature	420 - 450 Â°C	788 - 842 Â°F	
Mold Temperature	26.7 - 65.6 Â°C	80.0 - 150 Â°F	
Injection Pressure	3.45 - 4.83 MPa	500 - 700 psi	
Back Pressure	0.689 - 1.38 MPa	100 - 200 psi	

Descriptive Properties	Value	Comments
Ozone Resistance	No cracking	100 pphm, 72 hr, 38Â°C, ASTM D518/1149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China