

Kuraray SEPTONÂ® A4 Hot Melt Adhesive

Category : Polymer , Adhesive , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Description: SEPTONÂ® is a series of high performance thermoplastic rubbers developed by Kuraray Co. Ltd. Using its isoprene technology. SEPTONÂ® resins are a series of hydrogenated styrenic block copolymers, which exhibit rubber-like properties over a wide range of temperatures. SEPTONÂ®'s characteristics include:Excellent Mechanical PropertiesGood WeatherabilityExcellent Low Temperature PropertiesExcellent Electrical PropertiesSuperior Heat ResistanceExcellent Chemical ResistanceLow ToxicitySEPTONÂ® grades are available with a range of Shore A hardness of 35-95 and tensile strengths of 290-5600 psi. SEPTONÂ® resins are highly extendible with fillers, resins and oils, which allows formulation of a variety of hardness for adhesives, sealants and various compounds. As an additive, SEPTONÂ® resins can be used to improve toughness of a variety of plastics. Several SEPTONÂ® grades have U.S. FDA and USP Class VI approval.SEPTONÂ® has a versatile series of grades which can be used in numerous processing techniques such as blow molding, injection molding, extrusion, hot melt and solution coatings. SEPTONÂ® resins are thermoplastics therefore, the scrap is recyclable without significant loss of properties.When blended with a tackifier and a process oil, SEPTONÂ® polymers provide hot melt adhesives having excellent heat and weather resistance.SEPTONÂ® Solubility: Partial to Non-Soluble in: Ethyl Acetate, MEK, Methanol, Ethanol, Acetone, WaterSoluble in: Petroleum Ether, Toluene, Benzene, Hexane and CyclohexaneTackifiers Compatible with SEPTONÂ®:Rubber Phase: Acyclic Saturated Hydrocarbon resins, Hydrogenated Terpene resins, Petroleum resin and Hydrogenated Rosin resinStyrene Phase: Aromatic resins and Styrenic resinsFormulation (parts by weight): SEPTONÂ® 2004 - 100, Acyclic Saturated Hydrocarbon Resin - 300, Paraffinic Process Oil - 100 Information provided by The Kuraray Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-SEPTON-A4-Hot-Melt-Adhesive.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	4700 cP	4700 cP	melt viscosity

Mechanical Properties	Metric	English	Comments
Peel Strength	0.490 kN/m	2.80 pli	to polyethylene, 180Â° peel test, rate of peel = 300mm/min at 25Â°C
	1.354 kN/m	7.725 pli	to stainless steel, 180Â° peel test, rate of peel = 300mm/min at 25Â°C

Descriptive Properties	Value	Comments
Cohesion, Static Shear	min 240	load: 1 kg at 40Â°C, sample size: 25 mm x 25 mm
Rolling Ball Tack Test	2 balls (Max)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China