

Kuraray SEPTONÂ® S4030 Thermoplastic Rubber

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

SEPTONÂ® is a series of high performance thermoplastic rubbers developed by Kuraray Co. Ltd. using its isoprene technology. SEPTONÂ® resins are hydrogenated styrenic block copolymers, which exhibit rubber-like properties over a wide range of temperatures. SEPTONÂ®'s characteristics include:Excellent Mechanical PropertiesGood WeatherabilityExcellent Low Temperature PropertiesExcellent Electrical PropertiesSuperior Heat ResistanceExcellent Chemical ResistanceLow ToxicitySEPTONÂ® grades are available with a range of Shore A hardness of 35-95 and tensile strengths of 290-5600 psi. SEPTONÂ® resins are highly extendible with fillers, resins and oils, which allows formulation of a variety of hardness for adhesives, sealants and various compounds. As an additive, SEPTONÂ® resins can be used to improve toughness of a variety of plastics. Several SEPTONÂ® grades have U.S. FDA and USP Class VI approval. SEPTONÂ® has a versatile series of grades which can be used in numerous processing techniques such as blow molding, injection molding, extrusion, hot melt and solution coatings. SEPTONÂ® resins are thermoplastics therefore, the scrap is recyclable without significant loss of properties. Information provided by The Kuraray Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-SEPTON-S4030-Thermoplastic-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.890 g/cc	0.890 g/cc	ISO 1183
Viscosity	65 cP @Temperature 30.0 Â°C	65 cP @Temperature 86.0 Â°F	15% wt, Toluene Solution
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 230 Â°C	1.5 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	71	71	ISO 48
Tensile Strength, Ultimate	27.1 MPa	3930 psi	ISO 37
Elongation at Break	540 %	540 %	
100% Modulus	0.00200 GPa	0.290 ksi	ISO 37

Chemical Properties	Metric	English	Comments
Styrene Content	20 %	20 %	

Descriptive Properties	Value	Comments
Physical Form	Pellet	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China