

LATI Latamid 66 H2 G/25-V0KB PA 66, 25% Glass Fiber Reinforced, Heat Stabilized, Flame Retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Glass Fiber Filled, Flame Retardant

Material Notes:

Polyamide 66 (PA66) based compound. Heat stabilized. Glass fibers. UL94 V-0 classified, with red phosphorous. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latamid-66-H2-G25-V0KB-PA-66-25-Glass-Fiber-Reinforced-Heat-Stabilized-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	
Linear Mold Shrinkage, Flow	0.0035 - 0.0065 cm/cm	0.0035 - 0.0065 in/in	
Linear Mold Shrinkage, Transverse	0.0085 - 0.0115 cm/cm	0.0085 - 0.0115 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	70.0 MPa	10200 psi	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	85.0 MPa	12300 psi	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	115 MPa	16700 psi	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	145 MPa	21000 psi	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Elongation at Break	3.0 %	3.0 %	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	3.8 %	3.8 %	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	5.1 %	5.1 %	

Mechanical Properties	Metric	English	Comments
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	5.6 %	5.6 %	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	6.0 %	6.0 %	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
Tensile Modulus	4.00 GPa	580 ksi	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	4.70 GPa	682 ksi	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	5.40 GPa	783 ksi	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	7.80 GPa	1130 ksi	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	8.80 GPa	1280 ksi	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Charpy Impact Unnotched	7.00 J/cmÂ²	33.3 ft-lb/inÂ²	
Charpy Impact, Notched	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 Â°C	257 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	255 Â°C	491 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	230 Â°C	446 Â°F	
Vicat Softening Point	235 Â°C	455 Â°F	
	@Load 5.00 kg	@Load 11.0 lb	
Flammability, UL94	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	
	V-0	V-0	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Thermal Properties	V-0 Metric	V-0 English	Comments
	@Thickness 0.750 mm	@Thickness 0.0295 in	
Oxygen Index	27 %	27 %	
Glow Wire Test	750 Â°C	1380 Â°F	GWIT
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	750 Â°C	1380 Â°F	GWIT
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 Â°C	1760 Â°F	GWFI/GWT
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	960 Â°C	1760 Â°F	GWFI/GWT
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	400 V	400 V	A solution

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 290 Â°C	518 - 554 Â°F	
Mold Temperature	70.0 - 100 Â°C	158 - 212 Â°F	
Drying Temperature	90.0 - 100 Â°C	194 - 212 Â°F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China