

LATI Laticonther 62 CPG/500 PA 6, Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

High thermal conductivity product based on Polyamide 6 (PA6). Special filler. Glass fibers. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Laticonther-62-CPG500-PA-6-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.91 g/cc	0.0690 lb/in ³	
Linear Mold Shrinkage, Flow	0.0035 - 0.0060 cm/cm	0.0035 - 0.0060 in/in	
Linear Mold Shrinkage, Transverse	0.0045 - 0.0070 cm/cm	0.0045 - 0.0070 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	
Elongation at Break	2.0 %	2.0 %	
Tensile Modulus	8.50 GPa	1230 ksi	
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.20 W/m-K	8.33 BTU-in/hr-ft ² - °F	Longitudinal
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	
Vicat Softening Point	205 °C @Load 5.00 kg	401 °F @Load 11.0 lb	

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	90.0 - 100 Â°C	194 - 212 Â°F	
Drying Temperature	90.0 - 100 Â°C	194 - 212 Â°F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China