

LATI Latilub 66-01M G/30 PA66, 30% Glass Fiber Reinforced, Molybdenum disulphide Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Fiber/MoS2 Filled

Material Notes:

Self-lubricating product based on Polyamide 66 (PA66). Molybdenum disulphide. Glass fibers. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latilub-66-01M-G30-PA66-30-Glass-Fiber-Reinforced-Molybdenum-disulphide-Filled.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in ³	
Linear Mold Shrinkage, Flow	0.0035 - 0.0065 cm/cm	0.0035 - 0.0065 in/in	
Linear Mold Shrinkage, Transverse	0.0075 - 0.0105 cm/cm	0.0075 - 0.0105 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	165 MPa	23900 psi	
Elongation at Break	3.1 %	3.1 %	
Tensile Modulus	9.40 GPa	1360 ksi	
Charpy Impact Unnotched	6.50 J/cm ²	30.9 ft-lb/in ²	
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	
Coefficient of Friction, Dynamic	0.36	0.36	
Coefficient of Friction, Static	0.42	0.42	
K (wear) Factor	30.0 x 10 ⁻⁸ mm ³ /N-M	14.9 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	260 Â°C	500 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	255 Â°C	491 Â°F	
Vicat Softening Point	255 Â°C @Load 5.00 kg	491 Â°F @Load 11.0 lb	
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	

Processing Properties	Metric	English	Comments
Melt Temperature	275 - 300 Â°C	527 - 572 Â°F	
Mold Temperature	70.0 - 100 Â°C	158 - 212 Â°F	
Drying Temperature	90.0 - 100 Â°C @Time 10800 sec	194 - 212 Â°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China