

LG Chemical AF308 ABS, Flame Retardant

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Feature: Injection Molding, Flame Retardant
 Application: Electric/Electronic Applications (TV, Monitor Housing) IT/OA device
 CAS No. 9003-56-9, 40039-93-8 and 1309-64-4
 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-AF308-ABS-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Maximum Moisture Content	0.010	0.010	Injection Molding
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm @Thickness 3.20 mm	0.0040 - 0.0070 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	48 g/10 min @Load 10.0 kg, Temperature 220 Â°C	48 g/10 min @Load 22.0 lb, Temperature 428 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength, Yield	41.2 MPa @Thickness 3.20 mm	5970 psi @Thickness 0.126 in	50 mm/min; ASTM D638
Elongation at Break	25 % @Thickness 3.20 mm	25 % @Thickness 0.126 in	50 mm/min; ASTM D638
Elongation at Yield	>= 5.0 % @Thickness 3.20 mm	>= 5.0 % @Thickness 0.126 in	50 mm/min; ASTM D638
Tensile Modulus	2.16 GPa @Thickness 3.20 mm	313 ksi @Thickness 0.126 in	1 mm/min; ASTM D638
Flexural Yield Strength	66.7 MPa @Thickness 6.40 mm	9670 psi @Thickness 0.252 in	15 mm/min; ASTM D790
Flexural Modulus	2.35 GPa @Thickness 6.40 mm	341 ksi @Thickness 0.252 in	15 mm/min; ASTM D790
Izod Impact, Notched	1.77 J/cm @Thickness 6.40 mm,	3.31 ft-lb/in @Thickness 0.252 in,	ASTM D256

Mechanical Properties	Temperature 23.0 Â°C Metric	Temperature 73.4 Â°F English	Comments
	1.96 J/cm	3.67 ft-lb/in	
	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256
Izod Impact, Unnotched	0.686 J/cm	1.29 ft-lb/in	
	@Thickness 6.40 mm, Temperature -30.0 Â°C	@Thickness 0.252 in, Temperature -22.0 Â°F	ASTM D256
	0.686 J/cm	1.29 ft-lb/in	
	@Thickness 3.20 mm, Temperature -30.0 Â°C	@Thickness 0.126 in, Temperature -22.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 Â°C	194 Â°F	
	@Thickness 6.40 mm	@Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.0 Â°C	180 Â°F	
	@Thickness 6.40 mm	@Thickness 0.252 in	Unannealed; ASTM D648
Vicat Softening Point	90.0 Â°C	194 Â°F	
	@Load 5.00 kg	@Load 11.0 lb	50Â°C/h; ASTM D1525
UL RTI, Electrical	60.0 Â°C	140 Â°F	
	@Thickness >=1.80 mm	@Thickness >=0.0709 in	UL 746B
	60.0 Â°C	140 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
	60.0 Â°C	140 Â°F	
	@Thickness >=6.00 mm	@Thickness >=0.236 in	
UL RTI, Mechanical with Impact	60.0 Â°C	140 Â°F	
	@Thickness >=1.80 mm	@Thickness >=0.0709 in	UL 746B
	60.0 Â°C	140 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
	60.0 Â°C	140 Â°F	
	@Thickness >=6.00 mm	@Thickness >=0.236 in	
UL RTI, Mechanical without Impact	60.0 Â°C	140 Â°F	
	@Thickness >=1.80 mm	@Thickness >=0.0709 in	UL 746B

Thermal Properties	Metric	English	Comments
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
	60.0 Â°C	140 Â°F	
	@Thickness >=6.00 mm	@Thickness >=0.236 in	
Flammability, UL94	V-2	V-2	
	@Thickness >=1.80 mm	@Thickness >=0.0709 in	
	V-2	V-2	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
	V-2	V-2	
	@Thickness >=6.00 mm	@Thickness >=0.236 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Dielectric Strength	27.0 kV/mm	686 kV/in	
Arc Resistance	60 - 120 sec	60 - 120 sec	ASTM D495
Comparative Tracking Index	250 - 400 V	250 - 400 V	
Hot Wire Ignition, HWI	7.0 - 15 sec	7.0 - 15 sec	
	@Thickness >=1.80 mm	@Thickness >=0.0709 in	
	15 - 30 sec	15 - 30 sec	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
	60 - 120 sec	60 - 120 sec	
	@Thickness >=6.00 mm	@Thickness >=0.236 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	
	@Thickness 1.80 mm	@Thickness 0.0709 in	
	>= 120 arcs	>= 120 arcs	
	@Thickness 3.00 mm	@Thickness 0.118 in	
	>= 120 arcs	>= 120 arcs	
	@Thickness 6.00 mm	@Thickness 0.236 in	
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Middle Barrel Temperature	190 - 210 Â°C	374 - 410 Â°F	Injection Molding
Front Barrel Temperature	200 - 220 Â°C	392 - 428 Â°F	Injection Molding
Nozzle Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Melt Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Mold Temperature	40.0 - 60.0 Â°C	104 - 140 Â°F	Injection Molding
Drying Temperature	70.0 - 80.0 Â°C	158 - 176 Â°F	Injection Molding
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	Injection Molding
Back Pressure	0.490 - 0.981 MPa	71.1 - 142 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China