

LG Chemical AF360C ABS, TBBA-free Flame Retardant, High Flow

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Feature: Injection Molding, TBBA-free Flame Retardant, High Flow Application: Electric/Electronic Applications (TV, Monitor Housing)

IT/OA device CAS No. 9003-56-9 and 1309-64-4 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-AF360C-ABS-TBBA-free-Flame-Retardant-High-Flow.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Maximum Moisture Content	0.010	0.010	Injection Molding
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm @Thickness 3.20 mm	0.0040 - 0.0070 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	40 g/10 min @Load 10.0 kg, Temperature 220 Â°C	40 g/10 min @Load 22.0 lb, Temperature 428 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	101	101	ASTM D785
Tensile Strength, Yield	39.2 MPa @Thickness 3.20 mm	5690 psi @Thickness 0.126 in	50 mm/min; ASTM D638
Elongation at Break	20 % @Thickness 3.20 mm	20 % @Thickness 0.126 in	50 mm/min; ASTM D638
Elongation at Yield	>= 5.0 % @Thickness 3.20 mm	>= 5.0 % @Thickness 0.126 in	50 mm/min; ASTM D638
Tensile Modulus	2.26 GPa @Thickness 3.20 mm	327 ksi @Thickness 0.126 in	1 mm/min; ASTM D638
Flexural Yield Strength	68.6 MPa @Thickness 6.40 mm	9960 psi @Thickness 0.252 in	15 mm/min; ASTM D790
Flexural Modulus	2.40 GPa @Thickness 6.40 mm	348 ksi @Thickness 0.252 in	15 mm/min; ASTM D790
Izod Impact, Notched	1.67 J/cm @Thickness 6.40 mm,	3.12 ft-lb/in @Thickness 0.252 in,	ASTM D256

Mechanical Properties	Metric	English	Comments
Izod Impact, Unnotched	1.96 J/cm	3.67 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	
	0.686 J/cm	1.29 ft-lb/in	
Izod Impact, Unnotched	@Thickness 6.40 mm, Temperature -30.0 Â°C	@Thickness 0.252 in, Temperature -22.0 Â°F	ASTM D256
	0.686 J/cm	1.29 ft-lb/in	
	@Thickness 3.20 mm, Temperature -30.0 Â°C	@Thickness 0.126 in, Temperature -22.0 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	88.0 Â°C	190 Â°F	Unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	81.0 Â°C	178 Â°F	Unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	87.0 Â°C	189 Â°F	50Â°C/h; ASTM D1525
	@Load 5.00 kg	@Load 11.0 lb	
UL RTI, Electrical	60.0 Â°C	140 Â°F	UL 746B
UL RTI, Mechanical with Impact	60.0 Â°C	140 Â°F	UL 746B
UL RTI, Mechanical without Impact	60.0 Â°C	140 Â°F	UL 746B
Flammability, UL94	V-0	V-0	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	V-0	V-0	
Flammability, UL94	@Thickness >=2.00 mm	@Thickness >=0.0787 in	
	V-0	V-0	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	170 - 190 Â°C	338 - 374 Â°F	Injection Molding
Middle Barrel Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Front Barrel Temperature	190 - 210 Â°C	374 - 410 Â°F	Injection Molding

Nozzle Temperature Processing Properties	200 - 230 Â°C Metric	392 - 446 Â°F English	Injection Molding Comments
Melt Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Mold Temperature	40.0 - 60.0 Â°C	104 - 140 Â°F	Injection Molding
Drying Temperature	70.0 - 80.0 Â°C	158 - 176 Â°F	Injection Molding
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	Injection Molding
Back Pressure	0.490 - 0.981 MPa	71.1 - 142 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China