

LG Chemical EM505 Impact modifier for Engineering Plastics

Category : Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Description: LG Chem impact modifiers for Engineering Plastic are developed to enhance the impact strength of Engineering Plastics (PC, PBT, ABS, PC/PBT, PC/ABS, etc). LG Chem has 2 type impact modifiers - Butadien type, Acryl type. Application: PC Alloy (PC, PC/ABS, PC/PBT) etc. Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-EM505-Impact-modifier-for-Engineering-Plastics.php

Physical Properties	Metric	English	Comments
Bulk Density	>= 0.250 g/cc	>= 0.00903 lb/in ³	Aerated; LSY-QB-KD019
Volatiles	<= 1.0 %	<= 1.0 %	ISO 1625
Particle Mesh Size	20 Mesh	20 Mesh	<3%, (mesh on); LSY-QB-KD034
	200 Mesh	200 Mesh	<35%, (mesh pass); LSY-QB-KD035

Mechanical Properties	Metric	English	Comments
Izod Impact, Unnotched	>= 0.981 J/cm	>= 1.84 ft-lb/in	ISO 180
	@ Thickness 6.35 mm, Temperature -30.0 Â°C	@ Thickness 0.250 in, Temperature -22.0 Â°F	
	>= 3.92 J/cm	>= 7.35 ft-lb/in	ISO 180
	@ Thickness 3.17 mm, Temperature -30.0 Â°C	@ Thickness 0.125 in, Temperature -22.0 Â°F	
	>= 4.90 J/cm	>= 9.18 ft-lb/in	ISO 180
	@ Thickness 6.35 mm, Temperature 23.0 Â°C	@ Thickness 0.250 in, Temperature 73.4 Â°F	
	>= 5.88 J/cm	>= 11.0 ft-lb/in	ISO 180
	@ Thickness 3.17 mm, Temperature 23.0 Â°C	@ Thickness 0.125 in, Temperature 73.4 Â°F	

Descriptive Properties	Value	Comments
Foreign Material	<3 (10 x 10 cm)	LSY-QB-KD005
Fusion time	<90 sec	ISO 1830-6

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China