

LG Chemical HI121H ABS, High Stiffness

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Feature: Injection Molding, High Stiffness
Application: Electric & Electronic Products, Miscellaneous Goods
CAS No. 9003-56-9
Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-HI121H-ABS-High-Stiffness.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Maximum Moisture Content	0.010	0.010	Injection Molding
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm @Thickness 3.20 mm	0.0040 - 0.0070 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	23 g/10 min @Load 10.0 kg, Temperature 220 Â°C	23 g/10 min @Load 22.0 lb, Temperature 428 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	51.0 MPa @Thickness 3.20 mm	7400 psi @Thickness 0.126 in	50 mm/min; ASTM D638
Elongation at Break	30 % @Thickness 3.20 mm	30 % @Thickness 0.126 in	50 mm/min; ASTM D638
Tensile Modulus	2.22 GPa @Thickness 3.20 mm	321 ksi @Thickness 0.126 in	1 mm/min; ASTM D638
Flexural Yield Strength	78.5 MPa @Thickness 3.20 mm	11400 psi @Thickness 0.126 in	15 mm/min; ASTM D790
Flexural Modulus	2.75 GPa @Thickness 3.20 mm	398 ksi @Thickness 0.126 in	15 mm/min; ASTM D790
Izod Impact, Notched	1.96 J/cm @Thickness 6.40 mm, Temperature 23.0 Â°C	3.67 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Â°F	ASTM D256
	2.26 J/cm	4.22 ft-lb/in	ASTM D256

Mechanical Properties	Metric @Thickness 3.20 mm, Temperature 23.0 Â°C	English @Thickness 0.126 in, Temperature 73.4 Â°F	Comments
Izod Impact, Unnotched	0.785 J/cm @Thickness 6.40 mm, Temperature -30.0 Â°C	1.47 ft-lb/in @Thickness 0.252 in, Temperature -22.0 Â°F	ASTM D256
	0.785 J/cm @Thickness 3.20 mm, Temperature -30.0 Â°C	1.47 ft-lb/in @Thickness 0.126 in, Temperature -22.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	86.0 Â°C @Thickness 6.40 mm	187 Â°F @Thickness 0.252 in	Unannealed; ASTM D648
	90.0 Â°C @Thickness 6.40 mm	194 Â°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	94.0 Â°C @Load 5.00 kg	201 Â°F @Load 11.0 lb	50Â°C/h; ASTM D1525
UL RTI, Electrical	60.0 Â°C	140 Â°F	UL 746B
UL RTI, Mechanical with Impact	60.0 Â°C	140 Â°F	UL 746B
UL RTI, Mechanical without Impact	60.0 Â°C	140 Â°F	UL 746B

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	27.0 kV/mm	686 kV/in	ASTM D149
Arc Resistance	60 - 120 sec	60 - 120 sec	ASTM D495
Comparative Tracking Index	>= 600 V	>= 600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Middle Barrel Temperature	190 - 210 Â°C	374 - 410 Â°F	Injection Molding
Front Barrel Temperature	200 - 220 Â°C	392 - 428 Â°F	Injection Molding
Nozzle Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Melt Temperature	210 - 240 Â°C	410 - 464 Â°F	Injection Molding
Mold Temperature	40.0 - 70.0 Â°C	104 - 158 Â°F	Injection Molding

Processing Properties	Metric	English	Comments
Drying Temperature	100-110 °C	212-230 °F	Injection Molding
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	Injection Molding
Back Pressure	29.4 - 58.8 MPa	4260 - 8530 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China