

LG Chemical HI855H PMMA, Impact Resistant Grade

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Impact Modified, Molded

Material Notes:

Molding granule designed for greater impact strength combined with the outstanding properties of conventional acrylic materials
Features:
 Excellent transparency and elegance
 Weather resistance and chemical resistance
 Surface hardness and coloring property
 Superior electrical resistance and mechanical properties
 No harm caused
Applications: Automotive Parts: Rear lamp cover
 Turn signal lamp cover
 Indoor lamp cover
 Rear quarter glass
 Automotive badge
 Electric or Electronic Parts: LCD light guide plate
 Microwave oven door/front panel
 Cassette door
 VCR cover/front panel
 Car stereo panel
 Dial scale
 Light pipe
 Sheet: Signboard
 Showcase
 Light dome
 Aquarium
 Picture frame
 Lighting and Miscellaneous: Solid surface
 Lighting cover
 Ornaments
 Watch crystal
 Optical lens
 Piano keyboard
 Information Provided by LG Chem

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-HI855H-PMMA-Impact-Resistant-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ASTM D792
Water Absorption	0.40 %	0.40 %	24 hours; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Index of Compound	3.5 g/10 min @Load 3.80 kg, Temperature 230 Â°C	3.5 g/10 min @Load 8.38 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	42	42	ASTM D785
Tensile Strength at Break	39.0 MPa	5660 psi	ASTM D638
Elongation at Break	90 %	90 %	ASTM D638
Flexural Strength	69.0 MPa	10000 psi	ASTM D790
Flexural Modulus	1.824 GPa	264.6 ksi	ASTM D790
Izod Impact, Notched	0.491 J/cm	0.920 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 Âµm/m-Â°C @Temperature 20.0 Â°C	33.3 Âµin/in-Â°F @Temperature 68.0 Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	81.0 Â°C	178 Â°F	ASTM D648
Vicat Softening Point	91.0 Â°C	196 Â°F	1 kg; ASTM D1525

Thermal Properties	Metric	English	Comments
Annealing Point	60.0 - 70.0 Â°C	140 - 158 Â°F	3-5 hours

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542
Haze	1.0 % @Thickness 3.20 mm	1.0 % @Thickness 0.126 in	ASTM D1003
Transmission, Visible	91 % @Thickness 3.20 mm	91 % @Thickness 0.126 in	ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	ASTM D257
Dielectric Constant	3.5 @Frequency 60 Hz	3.5 @Frequency 60 Hz	ASTM D150
Dielectric Strength	15.0 kV/mm	381 kV/in	4kV/s; ASTM D149
Dissipation Factor	0.040 @Frequency 60 Hz	0.040 @Frequency 60 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Processing Temperature	210 - 250 Â°C	410 - 482 Â°F	Injection molding cylinder temperature
Mold Temperature	60.0 - 70.0 Â°C	140 - 158 Â°F	
Drying Temperature	60.0 - 70.0 Â°C	140 - 158 Â°F	
Dry Time	4 - 6 hour	4 - 6 hour	
Injection Pressure	49.0 - 108 MPa	7110 - 15700 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China