

LG Chemical KEYFLEX BT 1163D Ester Type TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester, TP , Polyester Thermoplastic Elastomer

Material Notes:

Description: Injection Molding, TPC-ET, General Purpose, High Modulus
Application: Cable & Wire Jackets, Hose & Tubing, Sheet
CAS: 37282-12-5
Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-KEYFLEX-BT-1163D-Ester-Type-TPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Water Absorption	0.50 % @Temperature 23.0 Â°C, Time 86400 sec	0.50 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Molecular Weight	458.458 g/mol	458.458 g/mol	
Maximum Moisture Content	0.010	0.010	Injection Molding
	0.010	0.010	Extrusion Molding
Linear Mold Shrinkage, Flow	0.011 - 0.015 cm/cm @Thickness 3.20 mm	0.011 - 0.015 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 230 Â°C	15 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	ASTM D2240
Tensile Strength at Break	37.3 MPa @Thickness 2.00 mm	5410 psi @Thickness 0.0787 in	50mm/min; ASTM D638
Elongation at Break	450 % @Thickness 2.00 mm	450 % @Thickness 0.0787 in	50mm/min; ASTM D638
Flexural Modulus	0.216 GPa @Thickness 6.40 mm	31.3 ksi @Thickness 0.252 in	15mm/min; ASTM D790
Izod Impact, Notched	0.981 J/cm @Thickness 6.40 mm, Temperature -40.0 Â°C	1.84 ft-lb/in @Thickness 0.252 in, Temperature -40.0 Â°F	ASTM D256

Mechanical Properties	^{MB} Metric	^{MB} English	Comments ASTM D256
	@Thickness 6.40 mm, Temperature 23.0 Â°C	@Thickness 0.252 in, Temperature 73.4 Â°F	
Tear Strength	157 kN/m	896 pli	50mm/min, at Break; ASTM D624

Thermal Properties	Metric	English	Comments
Melting Point	208 Â°C	406 Â°F	Peak
Boiling Point	140 - 230 Â°C	284 - 446 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C @Thickness 6.40 mm	230 Â°F @Thickness 0.252 in	Unannealed; ASTM D648
Flash Point	300 - 340 Â°C	572 - 644 Â°F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	ASTM D257
Dielectric Strength	26.0 kV/mm @Thickness 1.00 mm	660 kV/in @Thickness 0.0394 in	ASTM D149
Comparative Tracking Index	600 V	600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	210 - 230 Â°C	410 - 446 Â°F	Injection Molding
Middle Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	Injection Molding
Front Barrel Temperature	225 - 245 Â°C	437 - 473 Â°F	Injection Molding
Nozzle Temperature	225 - 245 Â°C	437 - 473 Â°F	Injection Molding
Zone 1	210 - 230 Â°C	410 - 446 Â°F	Extrusion Molding
Zone 2	215 - 235 Â°C	419 - 455 Â°F	Extrusion Molding
Zone 3	225 - 245 Â°C	437 - 473 Â°F	Extrusion Molding
Zone 4	225 - 245 Â°C	437 - 473 Â°F	Extrusion Molding
Adapter Temperature	225 - 245 Â°C	437 - 473 Â°F	Extrusion Molding
Die Temperature	215 - 255 Â°C	419 - 491 Â°F	Extrusion Molding
Melt Temperature	210 - 240 Â°C	410 - 464 Â°F	Injection Molding
	210 - 240 Â°C	410 - 464 Â°F	Extrusion Molding

Processing Properties	Metric	English	Comments
Drying Temperature	80.0 - 90.0 Â°C	176 - 194 Â°F	Injection Molding
	80.0 - 90.0 Â°C	176 - 194 Â°F	Extrusion Molding
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	Injection Molding
	3.00 - 4.00 hour	3.00 - 4.00 hour	Extrusion Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China