

LG Chemical LS080S PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Uncompounded

Material Notes:

General Description: LS080S, homopolymer made by suspension polymerization, can be applied to hard or semi-hard products. Main Applications: Hard sheets, films, fittings, injection molded products, bottles, innoxious films, innoxious containers, and food packaging.CAS No: 9002-86-2Information provided by LG Chemical

Order this product through the following link: http://www.lookpolymers.com/polymer_LG-Chemical-LS080S-PVC.php

Physical Properties	Metric	English	Comments	
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D790	
Bulk Density	0.520 - 0.600 g/cc	0.0188 - 0.0217 lb/in³	ASTM D1895	
Volatiles	<= 0.30 %	<= 0.30 %	ASTM D3030	
	@Temperature 110 °C, Time 3600 sec	@Temperature 230 °F, Time 1.00 hour		
Particle Mesh Size	45 Mesh	45 Mesh	<0.2%; ASTM D1921	
Molecular Weight	60000 - 150000 g/mol	60000 - 150000 g/mol		

Thermal Properties	Metric	English	Comments
Melting Point	302 °C	576 °F	

Descriptive Properties	Value	Comments
Autoignition Temperature	435°C	
Degree of Polymerization	750-850	30°C, JIS K 6720-2
K-Value	61	DIN53726 / ISO1628-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China