

LG Chemical LUMID EG2309B(W) PA66+GF30%, Chemical Resistance(CaCl₂, Ethylene Glycol)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Feature: Injection Molding, PA66+GF30%, Chemical Resistance(CaCl₂, Ethylene Glycol)Application: Radiator Tank, Intercooler TankCAS No. 32131-17-2, 65997-17-3 and 9010-79-9Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer_LG-Chemical-LUMID-EG2309BW-PA66GF30-Chemical-ResistanceCaCl₂-Ethylene-Glycol.php](http://www.lookpolymers.com/polymer_LG-Chemical-LUMID-EG2309BW-PA66GF30-Chemical-ResistanceCaCl2-Ethylene-Glycol.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.365 g/cc	1.365 g/cc	ASTM D792
Water Absorption	0.70 % @Temperature 23.0 Â°C, Time 86400 sec	0.70 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Maximum Moisture Content	0.090	0.090	Injection Molding
Linear Mold Shrinkage, Flow	0.0040 - 0.0090 cm/cm @Thickness 3.20 mm	0.0040 - 0.0090 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Yield	177 MPa @Thickness 3.20 mm	25600 psi @Thickness 0.126 in	5mm/min; ASTM D638
Elongation at Break	4.0 % @Thickness 3.20 mm	4.0 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	235 MPa @Thickness 3.20 mm	34100 psi @Thickness 0.126 in	2.8mm/min; ASTM D790
Flexural Modulus	7.65 GPa @Thickness 3.20 mm	1110 ksi @Thickness 0.126 in	2.8mm/min; ASTM D790
Izod Impact, Notched	0.981 J/cm @Thickness 6.40 mm, Temperature 23.0 Â°C	1.84 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Â°F	ASTM D256
	1.13 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	2.11 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$	16.7 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Melting Point	260 $\text{Å}^\circ\text{C}$	500 $\text{Å}^\circ\text{F}$	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	260 $\text{Å}^\circ\text{C}$ @Thickness 6.40 mm	500 $\text{Å}^\circ\text{F}$ @Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	250 $\text{Å}^\circ\text{C}$ @Thickness 6.40 mm	482 $\text{Å}^\circ\text{F}$ @Thickness 0.252 in	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Constant	4.0 @Frequency 1.00e+6 Hz	4.0 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	25.0 kV/mm @Thickness 1.00 mm	635 kV/in @Thickness 0.0394 in	ASTM D149

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 270 $\text{Å}^\circ\text{C}$	500 - 518 $\text{Å}^\circ\text{F}$	Injection Molding
Middle Barrel Temperature	270 - 285 $\text{Å}^\circ\text{C}$	518 - 545 $\text{Å}^\circ\text{F}$	Injection Molding
Front Barrel Temperature	270 - 290 $\text{Å}^\circ\text{C}$	518 - 554 $\text{Å}^\circ\text{F}$	Injection Molding
Nozzle Temperature	270 - 295 $\text{Å}^\circ\text{C}$	518 - 563 $\text{Å}^\circ\text{F}$	Injection Molding
Melt Temperature	270 - 295 $\text{Å}^\circ\text{C}$	518 - 563 $\text{Å}^\circ\text{F}$	Injection Molding
Mold Temperature	80.0 - 100 $\text{Å}^\circ\text{C}$	176 - 212 $\text{Å}^\circ\text{F}$	Injection Molding
Drying Temperature	80.0 - 100 $\text{Å}^\circ\text{C}$	176 - 212 $\text{Å}^\circ\text{F}$	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding
Back Pressure	29.4 - 58.8 MPa	4260 - 8530 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China