

LG Chemical LUMID GP2259AFL PA6+GF25%, Flame Retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

Feature: Injection Molding, PA6+GF25%, Flame Retardant Application: IT/OA (Connector) CAS No. 25038-54-4, 65997-17-3, 1163-19-5, 1309-64-4 and 138265-88-0 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUMID-GP2259AFL-PA6GF25-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ASTM D792
Water Absorption	0.70 % @Temperature 23.0 Â°C, Time 86400 sec	0.70 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 - 0.0090 cm/cm @Thickness 3.20 mm	0.0040 - 0.0090 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	127 MPa @Thickness 3.20 mm	18500 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	3.0 % @Thickness 3.20 mm	3.0 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	186 MPa @Thickness 3.20 mm	27000 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	8.53 GPa @Thickness 3.20 mm	1240 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.981 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	1.84 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	41.0 Âµm/m-Â°C	22.8 Âµin/in-Â°F	ASTM D696
Melting Point	220 Â°C	428 Â°F	ASTM D3418

Thermal Properties	Metric	English	Comments
	@Thickness 6.40 mm	@Thickness 0.252 in	
UL RTI, Electrical	90.0 Â°C	194 Â°F	
	@Thickness >=0.800 mm	@Thickness >=0.0315 in	
	90.0 Â°C	194 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
UL RTI, Mechanical with Impact	90.0 Â°C	194 Â°F	
	@Thickness >=0.800 mm	@Thickness >=0.0315 in	
	90.0 Â°C	194 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
UL RTI, Mechanical without Impact	90.0 Â°C	194 Â°F	
	@Thickness >=0.800 mm	@Thickness >=0.0315 in	
	90.0 Â°C	194 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
Flammability, UL94	V-2	V-2	
	@Thickness >=0.800 mm	@Thickness >=0.0315 in	
	V-2	V-2	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Constant	3.8	3.8	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	21.0 kV/mm	533 kV/in	
	@Thickness 1.00 mm	@Thickness 0.0394 in	ASTM D149
Arc Resistance	90 sec	90 sec	ASTM D495
Comparative Tracking Index	250 - 400 V	250 - 400 V	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Rear Barrel Temperature Processing Properties	250 - 270 Â°C Metric	482 - 518 Â°F English	Injection Molding Comments
Middle Barrel Temperature	260 - 280 Â°C	500 - 536 Â°F	Injection Molding
Front Barrel Temperature	260 - 280 Â°C	500 - 536 Â°F	Injection Molding
Nozzle Temperature	260 - 285 Â°C	500 - 545 Â°F	Injection Molding
Melt Temperature	260 - 280 Â°C	500 - 536 Â°F	Injection Molding
Mold Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Drying Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China