

LG Chemical LUMID GP2309A(W) PA6+GF30%, General Purpose

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

Feature: Injection Molding, PA6+GF30%, General Purpose Application: Automotive (Cooling Fan) CAS No. 25038-54-4 and 65997-17-

3 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUMID-GP2309AW-PA6GF30-General-Purpose.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Water Absorption	1.1 %	1.1 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 - 0.0090 cm/cm @Thickness 3.20 mm	0.0040 - 0.0090 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	162 MPa @Thickness 3.20 mm	23500 psi @Thickness 0.126 in	5mm/min; ASTM D638
Elongation at Break	4.5 % @Thickness 3.20 mm	4.5 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	255 MPa @Thickness 6.40 mm	37000 psi @Thickness 0.252 in	2.8mm/min; ASTM D790
Flexural Modulus	8.83 GPa @Thickness 6.40 mm	1280 ksi @Thickness 0.252 in	2.8mm/min; ASTM D790
Izod Impact, Notched	1.27 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	2.39 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	35.0 Âµm/m-Â°C	19.4 Âµin/in-Â°F	ASTM D696
Melting Point	220 Â°C	428 Â°F	ASTM D3418
Deflection Temperature at 1.8 MPa (264 psi)	210 Â°C @Thickness 6.40 mm	410 Â°F @Thickness 0.252 in	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Constant	3.8 @Frequency 1.00e+6 Hz	3.8 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	20.0 kV/mm @Thickness 1.00 mm	508 kV/in @Thickness 0.0394 in	ASTM D149
Arc Resistance	130 sec	130 sec	ASTM D495

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	250 - 270 Â°C	482 - 518 Â°F	Injection Molding
Middle Barrel Temperature	260 - 285 Â°C	500 - 545 Â°F	Injection Molding
Front Barrel Temperature	260 - 290 Â°C	500 - 554 Â°F	Injection Molding
Nozzle Temperature	260 - 290 Â°C	500 - 554 Â°F	Injection Molding
Melt Temperature	260 - 290 Â°C	500 - 554 Â°F	Injection Molding
Mold Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Drying Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China