

LG Chemical LUPOL GP1007FE Flame Retardant PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant

Material Notes:

Description: Injection Molding, FR PP, General Purpose, Flame Retardant Application: Electrical & Electronic, Automotive Parts CAS: 9003-07-0 and 1309-64-4 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUPOL-GP1007FE-Flame-Retardant-PP.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.016 - 0.018 cm/cm @Thickness 3.20 mm	0.016 - 0.018 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 230 Â°C	1.5 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.5 MPa @Thickness 3.20 mm	3700 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	>= 200 % @Thickness 3.20 mm	>= 200 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	29.4 MPa @Thickness 6.40 mm	4270 psi @Thickness 0.252 in	10mm/min; ASTM D790
Flexural Modulus	0.981 GPa @Thickness 6.40 mm	142 ksi @Thickness 0.252 in	10mm/min; ASTM D790
Izod Impact, Notched	>= 4.90 J/cm @Thickness 6.40 mm, Temperature 23.0 Â°C	>= 9.18 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C @Thickness 3.20 mm	230 Â°F @Thickness 0.126 in	Unannealed; ASTM D648
UL RTI, Electrical	65.0 Â°C	149 Â°F	

Thermal Properties	Metric @Thickness >=0.750 mm	English @Thickness >=0.0295 in	Comments
	120 Â°C	248 Â°F	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	120 Â°C	248 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
UL RTI, Mechanical with Impact	65.0 Â°C	149 Â°F	
	@Thickness >=0.750 mm	@Thickness >=0.0295 in	
	120 Â°C	248 Â°F	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	120 Â°C	248 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
UL RTI, Mechanical without Impact	65.0 Â°C	149 Â°F	
	@Thickness >=0.750 mm	@Thickness >=0.0295 in	
	120 Â°C	248 Â°F	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	120 Â°C	248 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
Flammability, UL94	V-2	V-2	
	@Thickness >=0.750 mm	@Thickness >=0.0295 in	
	V-2	V-2	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	V-2	V-2	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	

Electrical Properties	Metric	English	Comments
Arc Resistance	120 - 180 sec	120 - 180 sec	ASTM D495
	7.0 - 15 sec	7.0 - 15 sec	
Hot Wire Ignition, HWI	@Thickness >=0.750	@Thickness >=0.0295	

Electrical Properties	^{mm} Metric	ⁱⁿ English	Comments
	15 - 30 sec	15 - 30 sec	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	30 - 60 sec	30 - 60 sec	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	>= 120 arcs	>= 120 arcs	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	>= 120 arcs	>= 120 arcs	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Zone 1	230 - 245 Â°C	446 - 473 Â°F	Extrusion Molding
Zone 2	200 - 230 Â°C	392 - 446 Â°F	Extrusion Molding
Zone 3	220 - 240 Â°C	428 - 464 Â°F	Extrusion Molding
Zone 4	220 - 240 Â°C	428 - 464 Â°F	Extrusion Molding
Die Temperature	220 - 240 Â°C	428 - 464 Â°F	Extrusion Molding
Melt Temperature	230 - 245 Â°C	446 - 473 Â°F	Extrusion Molding
Drying Temperature	70.0 - 80.0 Â°C	158 - 176 Â°F	Injection Molding
Dry Time	3.00 - 5.00 hour	3.00 - 5.00 hour	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China