

LG Chemical LUPOY GP5006BH PC/ABS, Heat Resistance, Impact Strength

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC) , Polycarbonate, Impact Modified

Material Notes:

Description: Injection Molding, PC/ABS, Heat Resistance, Impact Strength, High ToughnessApplication: Miscellaneous GoodsCAS: 103598-77-2, 9003-56-9 and 181028-79-5Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUPOY-GP5006BH-PCABS-Heat-Resistance-Impact-Strength.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0050 - 0.0080 cm/cm @Thickness 3.20 mm	0.0050 - 0.0080 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	3.3 g/10 min @Load 2.16 kg, Temperature 250 Â°C	3.3 g/10 min @Load 4.76 lb, Temperature 482 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	56.9 MPa @Thickness 3.20 mm	8250 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	>= 100 % @Thickness 3.20 mm	>= 100 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	91.2 MPa @Thickness 3.20 mm	13200 psi @Thickness 0.126 in	10mm/min; ASTM D790
Flexural Modulus	2.26 GPa @Thickness 3.20 mm	327 ksi @Thickness 0.126 in	10mm/min; ASTM D790
Izod Impact, Notched	>= 5.39 J/cm @Thickness 3.20 mm, Temperature -30.0 Â°C	>= 10.1 ft-lb/in @Thickness 0.126 in, Temperature -22.0 Â°F	ASTM D256
	>= 7.06 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	>= 13.2 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Temperature at 1.8 MPa (264 psi)	116 Â°C	241 Â°F	Injection Molding; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	240 - 270 Â°C	464 - 518 Â°F	Injection Molding
Middle Barrel Temperature	245 - 275 Â°C	473 - 527 Â°F	Injection Molding
Front Barrel Temperature	245 - 275 Â°C	473 - 527 Â°F	Injection Molding
Nozzle Temperature	245 - 275 Â°C	473 - 527 Â°F	Injection Molding
Melt Temperature	250 - 275 Â°C	482 - 527 Â°F	Injection Molding
Mold Temperature	50.0 - 70.0 Â°C	122 - 158 Â°F	Injection Molding
Drying Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	Injection Molding
Screw Speed	40 - 70 rpm	40 - 70 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China