

LG Chemical LUSEP SP2306F SPS+GF30%, Flame Retardant

Category : Polymer , Thermoplastic , Polystyrene (PS) , Syndiotactic Polystyrene (SPS) , Syndiotactic Polystyrene (SPS) with Glass or Carbon Fiber

Material Notes:

Feature: Injection Molding, sPS+GF30%, Flame Retardant Application: Pump Units, Pick-up Lends Holder, etc CAS No. 9003-53-6, 68928-70-1, 1309-64-4 and 65997-17-3 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUSEP-SP2306F-SPSGF30-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0030 - 0.0090 cm/cm @Thickness 3.20 mm	0.0030 - 0.0090 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	113 MPa @Thickness 3.20 mm	16400 psi @Thickness 0.126 in	5mm/min; ASTM D638
Elongation at Break	2.0 % @Thickness 3.20 mm	2.0 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	186 MPa @Thickness 3.20 mm	27000 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	9.32 GPa @Thickness 3.20 mm	1350 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.686 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	1.29 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	260 Â°C @Thickness 6.40 mm	500 Â°F @Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	>= 230 Â°C @Thickness 6.40 mm	>= 446 Â°F @Thickness 0.252 in	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Dielectric Strength	31.0 kV/mm	787 kV/in	ASTM D149
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Comparative Tracking Index	400 - 600 V	400 - 600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	270 - 290 Â°C	518 - 554 Â°F	Injection Molding
Middle Barrel Temperature	280 - 310 Â°C	536 - 590 Â°F	Injection Molding
Front Barrel Temperature	290 - 310 Â°C	554 - 590 Â°F	Injection Molding
Nozzle Temperature	280 - 310 Â°C	536 - 590 Â°F	Injection Molding
Melt Temperature	280 - 310 Â°C	536 - 590 Â°F	Injection Molding
Mold Temperature	80.0 - 150 Â°C	176 - 302 Â°F	Injection Molding
Drying Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Dry Time	3.00 - 5.00 hour	3.00 - 5.00 hour	Injection Molding
Screw Speed	40 - 80 rpm	40 - 80 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China