

LG Chemical Lupox® SV-1120 General Purpose PBT, Unreinforced, High Molecular Weight, Extrusion

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Unreinforced, Molded

Material Notes:

LUPOX semi-crystalline thermoplastic PBT resins exhibit properties including high strength, rigidity and good resistance to fatigue and creep at elevated temperatures. Furthermore, LUPOX resins show minimal moisture absorption, excellent electrical properties, plus good chemical resistance against water, weak acid and many solvents. Applications: Automotive: Back beam, door frame garnish, distributor cap, rotor arm, head lamp actuator, bezel, door handle, ignition components, connectors, speed control device, window drive system Electrical and Electronic: Relay, lamp socket, solenoid and transformer bobbin, timer case, focus pack, refrigerator muffler, key top, condenser, switch, connector, electronic range door latch, zircon frame and blade, PC inlet socket Industrial Parts and Household Appliances: Pump case, oven handle, toaster and cooker housing, gear, insulator support and bracket, telecommunications cable splice closure, water meter housing, loose tube Information Provided by LG Chem

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupox-SV-1120-General-Purpose-PBT-Unreinforced-High-Molecular-Weight-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.021 cm/cm	0.021 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	54.0 MPa	7830 psi	ASTM D638
Elongation at Break	>= 200 %	>= 200 %	ASTM D638
Flexural Strength	83.0 MPa	12000 psi	ASTM D790
Flexural Modulus	2.45 GPa	355 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm @Temperature 23.0 Â°C	0.749 ft-lb/in @Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	154 Â°C	309 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	57.0 Â°C	135 Â°F	ASTM D648
Flammability, UL94	HB	HB	

Thermal Properties	@Thickness 0.750 mm Metric	@Thickness 0.0295 in English	Comments
Processing Properties	Metric	English	Comments
Rear Barrel Temperature	225 - 235 Â°C	437 - 455 Â°F	
Middle Barrel Temperature	230 - 240 Â°C	446 - 464 Â°F	
Front Barrel Temperature	235 - 245 Â°C	455 - 473 Â°F	
Nozzle Temperature	235 - 245 Â°C	455 - 473 Â°F	
Melt Temperature	235 - 245 Â°C	455 - 473 Â°F	
Mold Temperature	40.0 - 80.0 Â°C	104 - 176 Â°F	
Drying Temperature	120 Â°C	248 Â°F	dehumidifying dryer
	@Time 14400 sec	@Time 4.00 hour	
	140 Â°C	284 Â°F	dehumidifying dryer
	@Time 7200 sec	@Time 2.00 hour	
Injection Pressure	34.32 - 49.03 MPa	4978 - 7111 psi	Second
	39.23 - 68.65 MPa	5690 - 9957 psi	First
Back Pressure	0.000 - 3.92 MPa	0.000 - 569 psi	
Screw Speed	70 - 100 rpm	70 - 100 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China