

LG Chemical Lupoy 1301-10 Polycarbonate Resin

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Description: LUPOY PC 1301-10 resin is designed for extrusion and injection molding products. It exhibits an excellent physical property balance of heat resistance, transparency and impact strength. Main Characteristics: Medium viscosity and Good mold release. Applications: Non food containers, Appliances and Packaging applications. CAS: 103598-77-2. Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupoy-1301-10-Polycarbonate-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.32 % @Temperature 23.0 Â°C	0.32 % @Temperature 73.4 Â°F	equilibrium, 50% RH; ASTM D570
	0.15 % @Temperature 23.0 Â°C, Time 86400 sec	0.15 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.00050 - 0.00070 cm/cm	0.00050 - 0.00070 in/in	ASTM D955
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 Â°C	10 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	73	73	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	71.0 MPa	10300 psi	ASTM D638
Tensile Strength, Yield	60.0 MPa	8700 psi	50mm/min; ASTM D638
Elongation at Break	150 %	150 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Tensile Modulus	2.41 GPa	350 ksi	ASTM D638
Flexural Yield Strength	96.0 MPa	13900 psi	ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790

Mechanical Properties	9.074 J/cm Metric	17.00 ft-lb/in English	Comments
Izod Impact, Notched	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	0.25 mm notch; ASTM D256
Izod Impact, Unnotched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	ASTM D256
Dart Drop, Total Energy	87.0 J @Thickness 3.20 mm	64.2 ft-lb @Thickness 0.126 in	203m/min; ASTM D3763
Abrasion	45 @Load 1.00 kg	45 @Load 2.20 lb	[%], CS-10 F wheel, 500 cycles; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear	68.0 Âµm/m-Â°C @Temperature -40.0 - 82.0 Â°C	37.8 Âµin/in-Â°F @Temperature -40.0 - 180 Â°F	ASTM D696
Hot Ball Pressure Test	>= 125 Â°C	>= 257 Â°F	IEC 598-1
Deflection Temperature at 0.46 MPa (66 psi)	144 Â°C @Thickness 4.00 mm	291 Â°F @Thickness 0.157 in	Annealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	128 Â°C @Thickness 4.00 mm	262 Â°F @Thickness 0.157 in	Unannealed; ASTM D648
	141 Â°C @Thickness 4.00 mm	286 Â°F @Thickness 0.157 in	Annealed; ASTM D648
Vicat Softening Point	149 Â°C @Load 5.10 kg	300 Â°F @Load 11.2 lb	50Â°C/hr; ASTM D1525
Softening Point	150 - 200 Â°C	302 - 392 Â°F	melting point per MSDS
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	ASTM D635
	V-2 @Thickness 0.500 mm	V-2 @Thickness 0.0197 in	ASTM D635
	V-2 @Thickness 1.60 mm	V-2 @Thickness 0.0630 in	ASTM D635
	V-2 @Thickness 2.50 - 2.70	V-2 @Thickness 0.0984 -	ASTM D635

Thermal Properties	^{mm} Metric	^{0.106 in} English	Comments
Flash Point	>= 450 Â°C	>= 842 Â°F	
Oxygen Index	26 %	26 %	ASTM D2863
Glow Wire Test	850 Â°C @Thickness 2.00 mm, Time 5.00 sec	1560 Â°F @Thickness 0.0787 in, Time 0.00139 hour	IEC 695-2-1

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542
Haze	0.70 - 1.5 %	0.70 - 1.5 %	ASTM D1003
Transmission, Visible	89 %	89 %	ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+17 ohm-cm	2.00e+17 ohm-cm	ASTM D257
Dielectric Constant	3.0 @Frequency 60.0 Hz	3.0 @Frequency 60.0 Hz	ASTM D150
Dielectric Strength	17.0 kV/mm	432 kV/in	ASTM D149
Dissipation Factor	0.0010 @Frequency 60.0 Hz	0.0010 @Frequency 60.0 Hz	ASTM D150
Comparative Tracking Index	250 V @Thickness 2.00 mm	250 V @Thickness 0.0787 in	IEC 112

Descriptive Properties	Value	Comments
Autoignition Temperature	>450Â°C	
Average Extent of Burning	ASTM D635	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China