

LG Chemical Lupoy 1301V-10 Polycarbonate Resin

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Description: LUPOY PC 1301V-10 resin is designed for extrusion and injection molding products. It exhibits an excellent physical property balance of heat resistance, transparency and impact strength. Main Characteristics: Halogen free flame retardant, Medium viscosity and Good mold release. Applications: Electrical appliances, Electronic components and Phone plugs. CAS: 103598-77-2. Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupoy-1301V-10-Polycarbonate-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.32 %	0.32 %	equilibrium, 50% RH; ASTM D570
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	0.15 %	0.15 %	ASTM D570
	@Temperature 23.0 Â°C, Time 86400 sec	@Temperature 73.4 Â°F, Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.00050 - 0.00070 cm/cm	0.00050 - 0.00070 in/in	ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 Â°C	@Load 2.65 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	73	73	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	71.0 MPa	10300 psi	ASTM D638
Tensile Strength, Yield	60.0 MPa	8700 psi	50mm/min; ASTM D638
Elongation at Break	150 %	150 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Tensile Modulus	2.41 GPa	350 ksi	ASTM D638
Flexural Yield Strength	96.0 MPa	13900 psi	ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	0.25 mm notch; ASTM D256
Izod Impact, Unnotched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	ASTM D256
Dart Drop, Total Energy	87.0 J @Thickness 3.20 mm	64.2 ft-lb @Thickness 0.126 in	203m/min; ASTM D3763
Abrasion	45 @Load 1.00 kg	45 @Load 2.20 lb	[%], CS-10 F wheel, 500 cycles; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear	68.0 Âµm/m-Â°C @Temperature -40.0 - 82.0 Â°C	37.8 Âµin/in-Â°F @Temperature -40.0 - 180 Â°F	ASTM D696
Hot Ball Pressure Test	>= 125 Â°C	>= 257 Â°F	IEC 598-1
Deflection Temperature at 0.46 MPa (66 psi)	144 Â°C @Thickness 4.00 mm	291 Â°F @Thickness 0.157 in	Annealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	128 Â°C @Thickness 4.00 mm	262 Â°F @Thickness 0.157 in	Unannealed; ASTM D648
	141 Â°C @Thickness 4.00 mm	286 Â°F @Thickness 0.157 in	Annealed; ASTM D648
Vicat Softening Point	149 Â°C @Load 5.10 kg	300 Â°F @Load 11.2 lb	50Â°C/hr; ASTM D1525
Softening Point	150 - 200 Â°C	302 - 392 Â°F	melting point per MSDS
UL RTI, Electrical	125 Â°C @Thickness >=1.50 mm	257 Â°F @Thickness >=0.0591 in	
	125 Â°C @Thickness >=3.00 mm	257 Â°F @Thickness >=0.118 in	
UL RTI, Mechanical with Impact	115 Â°C @Thickness >=1.50 mm	239 Â°F @Thickness >=0.0591 in	
	115 Â°C	239 Â°F	

Thermal Properties	Metric @ Thickness >=3.00 mm	English @ Thickness >=0.118 in	Comments
UL RTI, Mechanical without Impact	125 Â°C @Thickness >=1.50 mm	257 Â°F @Thickness >=0.0591 in	
	125 Â°C @Thickness >=3.00 mm	257 Â°F @Thickness >=0.118 in	
Flammability, UL94	V-2 @Thickness 1.60 mm	V-2 @Thickness 0.0630 in	ASTM D635
	V-2 @Thickness 3.00 mm	V-2 @Thickness 0.118 in	ASTM D635
Flash Point	>= 450 Â°C	>= 842 Â°F	
Oxygen Index	26 %	26 %	ASTM D2863
Glow Wire Test	850 Â°C @Thickness 2.00 mm, Time 5.00 sec	1560 Â°F @Thickness 0.0787 in, Time 0.00139 hour	IEC 695-2-1

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542
Haze	0.70 - 1.5 %	0.70 - 1.5 %	ASTM D1003
Transmission, Visible	89 %	89 %	ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+17 ohm-cm	2.00e+17 ohm-cm	ASTM D257
Dielectric Constant	3.0 @Frequency 60.0 Hz	3.0 @Frequency 60.0 Hz	ASTM D150
Dielectric Strength	17.0 kV/mm	432 kV/in	ASTM D149
Dissipation Factor	0.0010 @Frequency 60.0 Hz	0.0010 @Frequency 60.0 Hz	ASTM D150
Arc Resistance	120 - 180 sec	120 - 180 sec	ASTM D495
Comparative Tracking Index	250 V @Thickness 2.00 mm	250 V @Thickness 0.0787 in	IEC 112
		30 - 60 sec	

Electrical Properties	Metric	English	Comments
	30 - 60 sec	@ Thickness >=0.0591 in	
	@Thickness >=1.50 mm		
	60 - 120 sec	60 - 120 sec	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	60 - 120 arcs	60 - 120 arcs	
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Voltage Arc-Tracking Rate, HVTR	25.4 - 50.0 mm/min	1.00 - 1.97 in/min	

Descriptive Properties	Value	Comments
Autoignition Temperature	>450Å°C	
Average Extent of Burning	ASTM D635	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China