

LG Chemical SG175NS ABS, Super Surface Gloss, General Anti-Static

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Feature: Injection Molding, Super Surface Gloss, General Anti-Static
Application: Electric & Electronic Products
CAS No. 9003-56-9
Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-SG175NS-ABS-Super-Surface-Gloss-General-Anti-Static.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Maximum Moisture Content	0.010	0.010	Injection Molding
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm @Thickness 3.20 mm	0.0040 - 0.0070 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	32 g/10 min @Load 10.0 kg, Temperature 220 Â°C	32 g/10 min @Load 22.0 lb, Temperature 428 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	107	107	ASTM D785
Tensile Strength, Yield	48.1 MPa @Thickness 3.20 mm	6970 psi @Thickness 0.126 in	50 mm/min; ASTM D638
Elongation at Break	25 % @Thickness 3.20 mm	25 % @Thickness 0.126 in	50 mm/min; ASTM D638
Flexural Yield Strength	78.5 MPa @Thickness 3.20 mm	11400 psi @Thickness 0.126 in	15 mm/min; ASTM D790
Flexural Modulus	2.55 GPa @Thickness 3.20 mm	370 ksi @Thickness 0.126 in	15 mm/min; ASTM D790
Izod Impact, Notched	2.16 J/cm @Thickness 6.40 mm, Temperature 23.0 Â°C	4.04 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Â°F	ASTM D256
	2.16 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	4.04 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	85.0 Â°C @Thickness 6.40 mm	185 Â°F @Thickness 0.252 in	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Arc Resistance	60 - 120 sec	60 - 120 sec	ASTM D495
Comparative Tracking Index	>= 600 V	>= 600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Middle Barrel Temperature	190 - 210 Â°C	374 - 410 Â°F	Injection Molding
Front Barrel Temperature	200 - 220 Â°C	392 - 428 Â°F	Injection Molding
Nozzle Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Melt Temperature	210 - 240 Â°C	410 - 464 Â°F	Injection Molding
Mold Temperature	40.0 - 70.0 Â°C	104 - 158 Â°F	Injection Molding
Drying Temperature	80.0 Â°C	176 Â°F	Injection Molding
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	Injection Molding
Back Pressure	29.4 - 58.8 MPa	4260 - 8530 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China