

LNP Lubricomp® EFL-4544 Polyetherimide, Glass Fiber Reinforcement, PTFE Lubricant (discontinued **)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Features: LubricatedForms: PelletsProcessing Method: Injection MoldingInformation provided by LNP, a GE Plastics Company.This data sheet is labeled Discontinued; however many LNP grades are still active under new names instituted after the SABIC purchase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LNP-Lubricomp-EFL-4544-Polyetherimide-Glass-Fiber-Reinforcement-PTFE-Lubricant-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.56 g/cc	1.56 g/cc	Method A; ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0070 cm/cm	0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	137 MPa	19900 psi	ASTM D638
Elongation at Break	2.2 %	2.2 %	ASTM D638
Flexural Strength	193 MPa	28000 psi	ASTM D790
Flexural Modulus	8.48 GPa	1230 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm @Thickness 3.18 mm	1.89 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	4.27 J/cm @Thickness 3.18 mm	8.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	360 - 366 °C	680 - 691 °F	
Mold Temperature	121 - 149 °C	250 - 300 °F	
Drying Temperature	121 - 149 °C	250 - 300 °F	
Dry Time	4 hour	4 hour	

Processing Properties	Metric	English	Comments
Back Pressure	0.345 - 0.689 MPa	50.0 - 99.9 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China