

LNP Thermocomp® JF-1006 BK8-115 Polyethersulfone, Glass Fiber Reinforcement (discontinued **)

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

Forms: Pellets Processing Method: Injection Molding Information provided by LNP, a GE Plastics Company. This data sheet is labeled Discontinued; however many LNP grades are still active under new names instituted after the SABIC purchase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LNP-Thermocomp-JF-1006-BK8-115-Polyethersulfone-Glass-Fiber-Reinforcement-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	Method A; ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	132 MPa	19100 psi	ASTM D638
Elongation at Break	2.4 %	2.4 %	ASTM D638
Flexural Strength	186 MPa	27000 psi	ASTM D790
Flexural Modulus	9.03 GPa	1310 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm @Thickness 3.18 mm	1.20 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	5.34 J/cm @Thickness 3.18 mm	10.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	212 °C	414 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	354 - 371 °C	669 - 700 °F	
Mold Temperature	135 - 149 °C	275 - 300 °F	
Drying Temperature	121 - 149 °C	250 - 300 °F	
Dry Time	4 hour	4 hour	

Processing Properties	Metric	English	Comments
Back Pressure	0.345 - 0.689 MPa	50.0 - 99.9 psi	

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China