

LTL Color Compounds ColorFast® FRPS200 Styrene, High Impact

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant , Polystyrene, Impact Modified

Material Notes:

V0/5VA high impact styreneAll information provided by LTL Color Compounds, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LTL-Color-Compounds-ColorFast-FRPS200-Styrene-High-Impact.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	0.125; ASTM D955
Melt Flow	6.5 g/10 min	6.5 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	61	61	ASTM D785
Tensile Strength at Break	24.8 MPa	3600 psi	2.0 in/min; ASTM D638
Tensile Strength, Yield	24.1 MPa	3500 psi	2.0 in/min; ASTM D638
Elongation at Break	35 %	35 %	2.0 in/min; ASTM D638
Flexural Modulus	2.00 GPa	290 ksi	2.0 in/min; ASTM D790
Izod Impact, Notched	0.961 J/cm	1.80 ft-lb/in	ASTM D256
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	86.1 °C	187 °F	Unannealed (0.250"); ASTM D648
Flammability, UL94	V-0	V-0	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	171 - 199 °C	340 - 390 °F	
Middle Barrel Temperature	193 - 227 °C	380 - 440 °F	
Front Barrel Temperature	218 - 254 °C	425 - 490 °F	
Nozzle Temperature	204 - 232 °C	400 - 450 °F	

Melt Temperature Processing Properties	204 - 238 °C Metric	400 - 460 °F English	Comments
Mold Temperature	10.0 - 71.1 °C	50.0 - 160 °F	
Drying Temperature	71.1 °C	160 °F	
Dry Time	2 - 4 hour	2 - 4 hour	nominal; maximum drying time of 8 hours
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Shot Size	40 - 60 %	40 - 60 %	
Vent Depth	0.00254 - 0.00762 cm	0.00100 - 0.00300 in	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China