

Lanxess Durethan® BKV 30 G H2.0 900116 Nylon 6, 30% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

PA 6, injection molding grade, 30% glass fibers, better surface finish and resistance to alcoholic calcium chloride-solution than BKV 30 H2.0, heat-stabilized, good heat-ageing resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Durethan-BKV-30-G-H20-900116-Nylon-6-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Water Absorption	6.5 %	6.5 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	1.9 %	1.9 %	23 ^o C/50% R.H.; Test Sim. to ISO 62
Viscosity Test	140 cm ³ /g	140 cm ³ /g	Viscosity number; ISO 307, 1157, 1628
Linear Mold Shrinkage, Flow	0.0027 cm/cm	0.0027 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0058 cm/cm	0.0058 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	110 MPa	16000 psi	Conditioned; ISO 527-1/-2
	180 MPa	26100 psi	ISO 527-1/-2
Elongation at Break	3.0 %	3.0 %	ISO 527-1/-2
	7.0 %	7.0 %	Conditioned; ISO 527-1/-2
Tensile Modulus	6.20 GPa	899 ksi	Conditioned; ISO 527-1/-2
	9.50 GPa	1380 ksi	ISO 527-1/-2
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 ^o C	@Temperature -22.0 ^o F	
	6.00 J/cm ²	28.6 ft-lb/in ²	Conditioned; ISO 179/1eU
	@Temperature -30.0 ^o C	@Temperature -22.0 ^o F	
	7.50 J/cm ²	35.7 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 ^o C	@Temperature 73.4 ^o F	
	7.50 J/cm ²	35.7 ft-lb/in ²	

Mechanical Properties	Metric	English	Comments
	@ Temperature 23.0 Â°C	@ Temperature 73.4 Â°F	Conditioned; ISO 179/1eU
Charpy Impact, Notched	<= 1.00 J/cmÂ²	<= 4.76 ft-lb/inÂ²	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ISO 179/1eA
	<= 1.00 J/cmÂ²	<= 4.76 ft-lb/inÂ²	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	Conditioned; ISO 179/1eA
	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	ISO 179/1eA
	1.30 J/cmÂ²	6.19 ft-lb/inÂ²	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	Conditioned; ISO 179/1eA
Impact	838	838	Puncture maximum force (N); ISO 6603-2
	735	735	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	Puncture maximum force (N); ISO 6603-2
Puncture Energy	2.60 J	1.92 ft-lb	ISO 6603-2
	2.20 J	1.62 ft-lb	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ISO 6603-2
	2.20 J	1.62 ft-lb	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	Conditioned; ISO 6603-2

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 Âµm/m-Â°C	16.7 Âµin/in-Â°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	80.0 Âµm/m-Â°C	44.4 Âµin/in-Â°F	ISO 11359-1/-2
Melting Point	221 Â°C	430 Â°F	10Â°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	215 Â°C	419 Â°F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	195 Â°C	383 Â°F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	80.0 Â°C	176 Â°F	ISO 75-1/-2
Vicat Softening Point	210 Â°C	410 Â°F	50Â°C/h 50N; ISO 306

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 1.60 mm	@Thickness 0.0630 in	IEC 60695-11-10
	HB	HB	IEC 60695-11-10
	@Thickness 3.20 mm	@Thickness 0.126 in	
Oxygen Index	23 %	23 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	Conditioned; IEC 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	4.3	4.3	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	4.3	4.3	Conditioned; IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	7.0	7.0	Conditioned; IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	31.0 kV/mm	787 kV/in	Conditioned; IEC 60243-1
	34.0 kV/mm	864 kV/in	IEC 60243-1
Dissipation Factor	0.0080	0.0080	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.017	0.017	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.050	0.050	Conditioned; IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.13	0.13	Conditioned; IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	

Comparative Tracking Index Electrical Properties	475 V Metric	475 V English	IEC 60112 Comments
---	-----------------	------------------	-----------------------

Descriptive Properties	Value	Comments
Additives	Release agent	
Features	Heat stabilized or stable to heat	
Form	Pellets	
ISO Shortname	ISO 1874-PA 6,MHR,14-100,GF30	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China