

Lanxess Durethan® BKV 30 H3.0 000000 Nylon 6, 30% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

PA 6, injection molding grade with 30% glass fibers, good heat-ageing resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Durethan-BKV-30-H30-000000-Nylon-6-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Water Absorption	7.0 %	7.0 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	2.1 %	2.1 %	23 [°] C/50% R.H.; Test Sim. to ISO 62
Viscosity Test	140 cm ³ /g	140 cm ³ /g	Viscosity number; ISO 307, 1157, 1628
Melt Flow	19 g/10 min @Load 5.00 kg, Temperature 260 [°] C	19 g/10 min @Load 11.0 lb, Temperature 500 [°] F	Estimated using room temperature density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	Conditioned; ISO 527-1/-2
	180 MPa	26100 psi	ISO 527-1/-2
Elongation at Break	3.0 %	3.0 %	ISO 527-1/-2
	6.0 %	6.0 %	Conditioned; ISO 527-1/-2
Tensile Modulus	6.10 GPa	885 ksi	Conditioned; ISO 527-1/-2
	9.80 GPa	1420 ksi	ISO 527-1/-2
Charpy Impact Unnotched	7.00 J/cm ² @Temperature -30.0 [°] C	33.3 ft-lb/in ² @Temperature -22.0 [°] F	ISO 179/1eU
	7.00 J/cm ² @Temperature -30.0 [°] C	33.3 ft-lb/in ² @Temperature -22.0 [°] F	Conditioned; ISO 179/1eU
	8.00 J/cm ² @Temperature 23.0 [°] C	38.1 ft-lb/in ² @Temperature 73.4 [°] F	ISO 179/1eU
	9.50 J/cm ²	45.2 ft-lb/in ²	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179/1eA
	1.00 J/cm ²	4.76 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	@Temperature -30.0 °C	@Temperature -22.0 °F	Conditioned; ISO 179/1eA
	1.50 J/cm ²	7.14 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	@Temperature -30.0 °C	@Temperature -22.0 °F	Conditioned; ISO 179/1eA
	2.00 J/cm ²	9.52 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Puncture Energy	8.00 J	5.90 ft-lb	ISO 6603-2
	14.0 J	10.3 ft-lb	Conditioned; ISO 6603-2
	6.00 J	4.43 ft-lb	
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 6603-2
	6.00 J	4.43 ft-lb	
	@Temperature -30.0 °C	@Temperature -22.0 °F	Conditioned; ISO 6603-2
Tensile Creep Modulus, 1 hour	5100 MPa	740000 psi	ISO 899-1
Tensile Creep Modulus, 1000 hours	4100 MPa	595000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
Melting Point	222 °C	432 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	110 °C	230 °F	ISO 75-1/-2
Vicat Softening Point	200 °C	392 °F	50°C/h 50N; ISO 306

Flammability, UL 94 Thermal Properties	HB Metric	HB English	IEC 60695-11-10 Comments
	HB	HB	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Oxygen Index	22 %	22 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	Conditioned; IEC 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	4.0	4.0	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	5.0	5.0	Conditioned; IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	15	15	Conditioned; IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	Conditioned; IEC 60243-1
	40.0 kV/mm	1020 kV/in	IEC 60243-1
Comparative Tracking Index	525 V	525 V	IEC 60112

Descriptive Properties	Value	Comments
Additives	Release agent	
Features	Heat stabilized or stable to heat	
Form	Pellets	
ISO Shortname	ISO 1874-PA 6,MHR,14-100,GF30	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	

Descriptive Properties	Near East/Africa Value	Comments
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China