

Lanxess Durethan® C 38 FKS 000000 Copolyamide

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Copolyamide, film quality, high transparency, with processing aid, nucleated
Application Examples: blown film coextrusion (outer layer)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Durethan-C-38-FKS-000000-Copolyamide.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ISO 1183
Water Absorption	10 %	10 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	3.0 %	3.0 %	23°C/50% R.H.; Test Sim. to ISO 62
Melt Flow	6 g/10 min @Load 2.16 kg, Temperature 235 °C	6 g/10 min @Load 4.76 lb, Temperature 455 °F	Estimated using room temperature density; ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	212 °C	414 °F	10°C/min; ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	Conditioned; IEC 60093
Surface Resistance	1.00e+11 ohm	1.00e+11 ohm	IEC 60093
Dielectric Constant	3.0 @Frequency 1.00e+6 Hz	3.0 @Frequency 1.00e+6 Hz	Conditioned; IEC 60250
Dielectric Strength	30.0 kV/mm	762 kV/in	Conditioned; IEC 60243-1

Descriptive Properties	Value	Comments
ISO Shortname	ISO 1874-PA 6/IPDI, FS,18-030N	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China