

Lanxess Pocan® B 4215 000000 PBT, 12% Glass Fiber

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 10% Glass Fiber Filled

Material Notes:

PBT, 12% glass fibers, injection molding, flame retardant

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Pocan-B-4215-000000-PBT-12-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.53 g/cc	0.0553 lb/in ³	ISO 1183
Water Absorption	0.30 %	0.30 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	0.10 %	0.10 %	23°C/50% R.H.; Test Sim. to ISO 62
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 260 °C	25 g/10 min @Load 4.76 lb, Temperature 500 °F	Calculated from MVR using melt density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	100 MPa	14500 psi	ISO 527-1/-2
Elongation at Break	2.5 %	2.5 %	ISO 527-1/-2
Tensile Modulus	5.70 GPa	827 ksi	ISO 527-1/-2
Charpy Impact Unnotched	3.00 J/cm ² @Temperature -30.0 °C	14.3 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	3.00 J/cm ² @Temperature 23.0 °C	14.3 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	<= 1.00 J/cm ² @Temperature -30.0 °C	<= 4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eA
	<= 1.00 J/cm ² @Temperature 23.0 °C	<= 4.76 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA
Tensile Creep Modulus, 1 hour	5500 MPa	798000 psi	ISO 899-1
Tensile Creep Modulus, 1000 hours	5000 MPa	725000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties to Flow	Metric $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	English $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Comments 1/-2
CTE, linear, Transverse to Flow	100 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	55.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-1/-2
Melting Point	225 $\text{Å}^\circ\text{C}$	437 $\text{Å}^\circ\text{F}$	10 $\text{Å}^\circ\text{C}/\text{min}$; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	205 $\text{Å}^\circ\text{C}$	401 $\text{Å}^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	185 $\text{Å}^\circ\text{C}$	365 $\text{Å}^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	70.0 $\text{Å}^\circ\text{C}$	158 $\text{Å}^\circ\text{F}$	ISO 75-1/-2
Vicat Softening Point	205 $\text{Å}^\circ\text{C}$	401 $\text{Å}^\circ\text{F}$	50 $\text{Å}^\circ\text{C}/\text{h}$ 50N; ISO 306
Flammability, UL94	V-2	V-2	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	V-0	V-0	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	5VA	5VA	IEC 60695-11-20
	@Thickness 3.50 mm	@Thickness 0.138 in	
Oxygen Index	32 %	32 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+13$ ohm-cm	$\geq 1.00\text{e}+13$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	IEC 60093
Dielectric Constant	3.4	3.4	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.6	3.6	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	29.0 kV/mm	737 kV/in	IEC 60243-1
Dissipation Factor	0.0040	0.0040	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.019	0.019	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	200 V	200 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	260 Â°C	500 Â°F	Injection Molding; ISO 294
Mold Temperature	80.0 Â°C	176 Â°F	Injection Molding; ISO 10724

Descriptive Properties	Value	Comments
Features	Flame retardant	
Form	Pellets	
ISO Shortname	ISO 7792-1-PBT,GFHMR,09-060,GF12; ISO 1043-PBT GF FR(17)	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China