

Lanxess Pocan® DP B 3235 XF 901510 PBT, 30% Glass Fiber (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

PBT, 30% glass fibers, injection molding, improved flowability

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Pocan-DP-B-3235-XF-901510-PBT-30-Glass-Fiber-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ISO 1183
Water Absorption	0.40 %	0.40 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	0.10 %	0.10 %	23°C/50% R.H.; Test Sim. to ISO 62
Melt Flow	44 g/10 min @Load 2.16 kg, Temperature 260 °C	44 g/10 min @Load 4.76 lb, Temperature 500 °F	Estimated using room temperature density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	ISO 527-1/-2
Elongation at Break	2.7 %	2.7 %	ISO 527-1/-2
Tensile Modulus	9.20 GPa	1330 ksi	ISO 527-1/-2
Charpy Impact Unnotched	6.00 J/cm ² @Temperature -30.0 °C	28.6 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	6.00 J/cm ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 µm/m-°C	16.7 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	130 µm/m-°C	72.2 µin/in-°F	ISO 11359-1/-2
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	150 °C	302 °F	ISO 75-1/-2
Flammability, UL94			IEC 60695-11-10

Thermal Properties	^{HB} Metric	^{HB} English	Comments
	HB	HB	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	525 V	525 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	260 °C	500 °F	Injection Molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection Molding; ISO 10724

Descriptive Properties	Value	Comments
Form	Pellets	
ISO Shortname	ISO 7792-PBT, MHR, -090, GF30	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China