

Lehmann & Voss LUVOCOM® 1-7789/EG Polyamide 66, with carbon fiber, lubricant modified, heat stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Carbon Fiber/PTFE Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Strong, stiff parts. Reduced moment of inertia compared with metal parts. Antistatic. High dimensionally stable precision parts with low warpage and narrow tolerance range. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1-7789EG-Polyamide-66-with-carbon-fiber-lubricant-modified-heat-stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	170 MPa	24700 psi	
Elongation at Yield	3.5 %	3.5 %	
	4.5 %	4.5 %	flexural
Modulus of Elasticity	9.00 GPa	1310 ksi	
Flexural Strength	245 MPa	35500 psi	
Flexural Modulus	8.00 GPa	1160 ksi	
Charpy Impact Unnotched	6.00 J/cmÂ²	28.6 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 Â°C	248 Â°F	
	160 Â°C	320 Â°F	short term

Electrical Properties	Metric	English	Comments
Insulation Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	290 Â°C	554 Â°F	mass temp

Processing Properties	Metric	English	Comments
Nozzle Temperature	280 - 300 Â°C	536 - 572 Â°F	
Zone 1	290 - 310 Â°C	554 - 590 Â°F	
Zone 2	290 - 310 Â°C	554 - 590 Â°F	
Zone 3	290 - 310 Â°C	554 - 590 Â°F	
Mold Temperature	90.0 - 120 Â°C	194 - 248 Â°F	
Drying Temperature	75.0 Â°C	167 Â°F	Dehumidifying dryer
	@Time 21600 - 57600 sec	@Time 6.00 - 16.0 hour	
	105 Â°C	221 Â°F	Vacuum Dryer
	@Time 14400 - 21600 sec	@Time 4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	black-grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China