

Lehmann & Voss LUVOCOM® 1-8228 Polyamide 66, lubricant modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Improved friction and wear behaviour. Emergency running property. Isotropic shrinkage characteristics. Bearings, sleeves, sliding elements, control disks, gear wheels, duty parts in switches. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1-8228-Polyamide-66-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23°C/24h
Linear Mold Shrinkage	0.011 - 0.016 cm/cm	0.011 - 0.016 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	80.0 MPa	11600 psi	
Elongation at Yield	4.3 %	4.3 %	
	5.5 %	5.5 %	flexural
Modulus of Elasticity	4.00 GPa	580 ksi	
Flexural Strength	115 MPa	16700 psi	
Flexural Modulus	3.00 GPa	435 ksi	
Charpy Impact Unnotched	3.00 J/cm ²	14.3 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	110 °C	230 °F	
	160 °C	320 °F	short term
Vicat Softening Point	220 °C	428 °F	DIN ISO 306

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	290 °C	554 °F	mass temp
Nozzle Temperature	280 - 300 °C	536 - 572 °F	
Zone 1	290 - 310 °C	554 - 590 °F	
Zone 2	290 - 310 °C	554 - 590 °F	
Zone 3	290 - 310 °C	554 - 590 °F	
Mold Temperature	90.0 - 120 °C	194 - 248 °F	
Drying Temperature	75.0 °C	167 °F	Dehumidifying dryer
	@Time 21600 - 57600 sec	@Time 6.00 - 16.0 hour	
	105 °C	221 °F	Vacuum Dryer
	@Time 14400 - 21600 sec	@Time 4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	dark grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China