

Lehmann & Voss LUVOCOM® 1105-7766 PEEK, with carbon fiber, easy flowing

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry. High-strength and high-stiff parts; low coefficient of expansion. Dynamic stressed parts at high movement velocity. Chemical and hydrolysis resistance parts, non flammable. Electrically conductive, suitable for continuous discharging of statically generated electricity. Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-7766-PEEK-with-carbon-fiber-easy-flowing.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.42 g/cc	1.42 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.00050 - 0.0020 cm/cm	0.00050 - 0.0020 in/in	
Melt Flow	21.3 g/10 min @Load 2.16 kg, Temperature 380 Â°C	21.3 g/10 min @Load 4.76 lb, Temperature 716 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	260 MPa	37700 psi	
Elongation at Yield	1.6 %	1.6 %	
	2.1 %	2.1 %	flexural
Modulus of Elasticity	27.0 GPa	3920 ksi	
Flexural Strength	375 MPa	54400 psi	
Flexural Modulus	22.95 GPa	3329 ksi	
Charpy Impact Unnotched	2.50 J/cmÂ²	11.9 ft-lb/inÂ²	flatwise; ISO 179 1fU
Charpy Impact, Notched	0.700 J/cmÂ²	3.33 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
CTE, linear	9.00 Âµm/m-Â°C	5.00 Âµin/in-Â°F	DIN 53752
Thermal Conductivity	0.600 W/m-K	4.16 BTU-in/hr-ftÂ²-Â°F	DIN 52612

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	280 Â°C	536 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	260 Â°C	500 Â°F	
Vicat Softening Point	320 Â°C	608 Â°F	DIN ISO 306
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 10000 ohm	<= 10000 ohm	
Insulation Resistance	<= 100000 ohm	<= 100000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C @Time 21600 - 28800 sec	248 Â°F @Time 6.00 - 8.00 hour	or
	150 Â°C @Time 10800 - 21600 sec	302 Â°F @Time 3.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China