

Lehmann & Voss LUVOCOM® 1105-7905 PEEK, with carbon fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry.Strong, stiff parts.Dynamic stressed parts at high movement velocity.High chemical resistance parts, hydrolysis resistance, non flammable.Electrically conductive, suitable for continuous discharging of statically generated electricity.Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-7905-PEEK-with-carbon-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	215 MPa	31200 psi	
Elongation at Yield	2.2 %	2.2 %	
	2.9 %	2.9 %	flexural
Modulus of Elasticity	16.0 GPa	2320 ksi	
Flexural Strength	310 MPa	45000 psi	
Flexural Modulus	14.0 GPa	2030 ksi	
Charpy Impact Unnotched	5.00 J/cmÂ²	23.8 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	280 Â°C	536 Â°F	short term

Electrical Properties	Metric	English	Comments
Insulation Resistance	<= 10000 ohm	<= 10000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp

Processing Properties	Metric	English	Comments
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C @Time 21600 - 28800 sec	248 Â°F @Time 6.00 - 8.00 hour	or
	150 Â°C @Time 10800 - 21600 sec	302 Â°F @Time 3.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China