

Lehmann & Voss LUVOCOM® 1105-8065 PEEK, with carbon fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry.Strong, stiff parts.Dynamic stressed parts at high movement velocity.High chemical resistance parts, hydrolysis resistance, non flammable.Electrically conductive, suitable for continuous discharging of statically generated electricity.Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-8065-PEEK-with-carbon-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	
Melt Flow	32.64 g/10 min @Load 10.0 kg, Temperature 380 Â°C	32.64 g/10 min @Load 22.0 lb, Temperature 716 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	200 MPa	29000 psi	
Elongation at Yield	2.3 %	2.3 %	
	2.6 %	2.6 %	flexural
Modulus of Elasticity	13.0 GPa	1890 ksi	
Flexural Strength	295 MPa	42800 psi	
Flexural Modulus	11.0 GPa	1600 ksi	
Charpy Impact Unnotched	4.80 J/cmÂ²	22.8 ft-lb/inÂ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	0.600 J/cmÂ²	2.86 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	280 Â°C	536 Â°F	short term

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Surface Resistance Electrical Properties	$\leq 1.00\text{e}+7$ ohm Metric	$\leq 1.00\text{e}+7$ ohm English	Comments
Insulation Resistance	$\leq 1.00\text{e}+7$ ohm	$\leq 1.00\text{e}+7$ ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China