

Lehmann & Voss LUVOCOM® 1105-8135/GN PEEK, unreinforced, easy flowing

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry. Especially suitable for medical parts, superheated steam sterilizable, hydrolysis resistance. High chemical resistance parts, non flammable. Inherent flame resistance. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-8135GN-PEEK-unreinforced-easy-flowing.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ISO 1183
Water Absorption	<= 0.50 %	<= 0.50 %	23Â°C/24h
Linear Mold Shrinkage	0.010 - 0.016 cm/cm	0.010 - 0.016 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	100 MPa	14500 psi	
Elongation at Yield	4.5 %	4.5 %	
	6.0 %	6.0 %	flexural
Modulus of Elasticity	4.00 GPa	580 ksi	
Flexural Strength	140 MPa	20300 psi	
Flexural Modulus	3.00 GPa	435 ksi	
Charpy Impact Unnotched	9.00 J/cmÂ²	42.8 ft-lb/inÂ²	flatwise; ISO 179 1fU
Charpy Impact, Notched	0.400 J/cmÂ²	1.90 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	260 Â°C	500 Â°F	short term
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	neon green	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China