

Lehmann & Voss LUVOCOM® 1106-7940/GY/EM Polyether imide, unreinforced, laser markable

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Applications: High continuous use and heat distortion temperature. Non flammable. Dynamic stressed parts at high movement velocity. High dimensionally stable precision parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1106-7940GYEM-Polyether-imide-unreinforced-laser-markable.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23Â°C/24h
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	115 MPa	16700 psi	
Elongation at Yield	6.5 %	6.5 %	
	8.0 %	8.0 %	flexural
Modulus of Elasticity	3.80 GPa	551 ksi	
Flexural Strength	165 MPa	23900 psi	
Flexural Modulus	3.30 GPa	479 ksi	
Charpy Impact Unnotched	8.50 J/cmÂ²	40.4 ft-lb/inÂ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	0.500 J/cmÂ²	2.38 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	170 Â°C	338 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	200 Â°C	392 Â°F	
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Electrical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	380 Â°C	716 Â°F	mass temp
Nozzle Temperature	350 - 400 Â°C	662 - 752 Â°F	
Zone 1	330 - 350 Â°C	626 - 662 Â°F	
Zone 2	340 - 390 Â°C	644 - 734 Â°F	
Zone 3	350 - 400 Â°C	662 - 752 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	120 Â°C	248 Â°F	Dehumidifying dryer
	@Time >=28800 sec	@Time >=8.00 hour	
	150 Â°C	302 Â°F	or
	@Time >=14400 sec	@Time >=4.00 hour	

Descriptive Properties	Value	Comments
Color	light grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China