

Lehmann & Voss LUVOCOM® 1301-7815 PPS, linear, with carbon fiber, lubricant modified

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 10% Carbon Fiber Filler

Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering.Improved friction and wear behaviour.
Emergency running property.Strong, stiff parts.Electrically conductive, suitable for continuous discharging of statically generated electricity.Suitable for metall inserts.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-7815-PPS-linear-with-carbon-fiber-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.65 g/cc	1.65 g/cc	ISO 1183
Water Absorption	<= 0.050 %	<= 0.050 %	23Â°C/24h
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	
Melt Flow	21.45 g/10 min @Load 2.16 kg, Temperature 300 Â°C	21.45 g/10 min @Load 4.76 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	135 MPa	19600 psi	
Elongation at Yield	1.2 %	1.2 %	
	1.6 %	1.6 %	flexural
Modulus of Elasticity	15.0 GPa	2180 ksi	
Flexural Strength	195 MPa	28300 psi	
Flexural Modulus	13.0 GPa	1890 ksi	
Charpy Impact Unnotched	1.80 J/cmÂ²	8.57 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 Â°C	428 Â°F	
	240 Â°C	464 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	

Insulation Resistance Electrical Properties	$\leq 1.00\text{e}+6\text{ ohm}$ Metric	$\leq 1.00\text{e}+6\text{ ohm}$ English	Comments
--	--	---	----------

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp
Nozzle Temperature	320 - 340 Â°C	608 - 644 Â°F	
Zone 1	300 - 320 Â°C	572 - 608 Â°F	
Zone 2	310 - 330 Â°C	590 - 626 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	50.0 - 90.0 Â°C @Time >= 14400 sec	122 - 194 Â°F @Time >= 4.00 hour	
	100 - 140 Â°C @Time 7200 - 14400 sec	212 - 284 Â°F @Time 2.00 - 4.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China