

Lehmann & Voss LUVOCOM® 1301-8066 PPS, linear, with carbon fiber, lubricant modified, high viscosity

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 10% Carbon Fiber Filler

Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering.High continuous use and heat distortion temperature. Non flammable.High-strength and stiff parts with low creep.Electrically conductive, suitable for continuous discharging of statically generated electricity.Suitable for metall inserts.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-8066-PPS-linear-with-carbon-fiber-lubricant-modified-high-viscosity.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.56 g/cc	1.56 g/cc	ISO 1183
Water Absorption	<= 0.050 %	<= 0.050 %	23Â°C/24h
Linear Mold Shrinkage	0.00050 - 0.0030 cm/cm	0.00050 - 0.0030 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	170 MPa	24700 psi	
Elongation at Yield	1.3 %	1.3 %	
	1.6 %	1.6 %	flexural
Modulus of Elasticity	21.0 GPa	3050 ksi	
Flexural Strength	240 MPa	34800 psi	
Flexural Modulus	18.0 GPa	2610 ksi	
Charpy Impact Unnotched	3.50 J/cmÂ²	16.7 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 Â°C	428 Â°F	
	240 Â°C	464 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1000 ohm	<= 1000 ohm	
Insulation Resistance	<= 1000 ohm	<= 1000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp
Nozzle Temperature	320 - 340 Â°C	608 - 644 Â°F	
Zone 1	300 - 320 Â°C	572 - 608 Â°F	
Zone 2	310 - 330 Â°C	590 - 626 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	50.0 - 90.0 Â°C	122 - 194 Â°F	
	@Time >= 14400 sec	@Time >= 4.00 hour	
	100 - 140 Â°C	212 - 284 Â°F	Dehumidifying dryer
	@Time 7200 - 14400 sec	@Time 2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	dark grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China