

Lehmann & Voss LUVOCOM® 1301-8386 PPS, linear, with aramid reinforcement and PTFE

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), Aramid Fiber Filled

Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering.Improved friction and wear behaviour.

Emergency running property.Low warpage.dynamic stressInformation provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-8386-PPS-linear-with-aramid-reinforcement-and-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.47 g/cc	1.47 g/cc	ISO 1183
Water Absorption	<= 0.20 %	<= 0.20 %	23Â°C/24h
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	70.0 MPa	10200 psi	
Elongation at Yield	1.6 %	1.6 %	
	2.1 %	2.1 %	flexural
Modulus of Elasticity	6.00 GPa	870 ksi	
Flexural Strength	100 MPa	14500 psi	
Flexural Modulus	5.00 GPa	725 ksi	
Charpy Impact Unnotched	1.20 J/cmÂ²	5.71 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 Â°C	428 Â°F	
	240 Â°C	464 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp

Processing Properties	Metric	English	Comments
	113 - 340 Â°C	509 - 644 Â°F	
Zone 1	300 - 320 Â°C	572 - 608 Â°F	
Zone 2	310 - 330 Â°C	590 - 626 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	50.0 - 90.0 Â°C	122 - 194 Â°F	
	@Time >=14400 sec	@Time >=4.00 hour	
	100 - 140 Â°C	212 - 284 Â°F	Dehumidifying dryer
	@Time 7200 - 14400 sec	@Time 2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	natural color (yellow)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China