

Lehmann & Voss LUVOCOM® 19-8043 Polyamide 46, with PTFE, lubricant modified, high viscosity

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Improved friction and wear behaviour. Emergency running property. Isotropic shrinkage characteristics. Bearings, sleeves, sliding elements, control disks, gear wheels, duty parts in switches. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-19-8043-Polyamide-46-with-PTFE-lubricant-modified-high-viscosity.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.013 - 0.020 cm/cm	0.013 - 0.020 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	75.0 MPa	10900 psi	
Elongation at Yield	5.5 %	5.5 %	
	6.5 %	6.5 %	flexural
Modulus of Elasticity	3.00 GPa	435 ksi	
Flexural Strength	110 MPa	16000 psi	
Flexural Modulus	2.50 GPa	363 ksi	
Charpy Impact Unnotched	4.50 J/cmÂ²	21.4 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 Â°C	302 Â°F	
	160 Â°C	320 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	310 Â°C	590 Â°F	mass temp
Nozzle Temperature	280 - 330 Â°C	536 - 626 Â°F	
Zone 1	285 - 315 Â°C	545 - 599 Â°F	
Zone 2	305 - 315 Â°C	581 - 599 Â°F	
Zone 3	305 - 315 Â°C	581 - 599 Â°F	
Mold Temperature	120 - 140 Â°C	248 - 284 Â°F	
Drying Temperature	80.0 Â°C	176 Â°F	Vacuum Dryer
	@Time 7200 - 43200 sec	@Time 2.00 - 12.0 hour	
	80.0 Â°C	176 Â°F	Dehumidifying dryer
	@Time 7200 - 28800 sec	@Time 2.00 - 8.00 hour	

Descriptive Properties	Value	Comments
Color	slate grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China